

MINFILE Number:	082ESE032	Name:	GOLDEN CROWN (L.600)	Status:	Past Producer
------------------------	-----------	--------------	----------------------	----------------	---------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
GOLDEN CROWN 2016 Y	163 kt Indicated	Gold Copper	11.09 g/t 0.56 %	using a 3.50 gram per tonne gold equivalent cut-off grade Cowley, P. (2017-06-02): Updated Preliminary Economic Assessment on the Greenwood Precious Metals Project
GOLDEN CROWN 2016 Y	42 kt Inferred	Gold Copper	9.04 g/t 0.43 %	using a 3.50 gram per tonne gold equivalent cut-off grade Cowley, P. (2017-06-02): Updated Preliminary Economic Assessment on the Greenwood Precious Metals Project
GOLDEN CROWN 2006 Y	105 kt Indicated	Gold Copper	13.78 g/t 0.55 %	an updated NI43-101 compliant indicated resource of 105,000 tonnes grading 13.78 grams per tonne gold and 0.55 per cent copper, or a gold equivalent of 15.33 grams per tonne was reported at a cut-off of 6.0 grams per tonne gold equivalent. This is believed to include the Winnipeg (L.599) (MINFILE 082ESE033) occurrence. Property File - Merit Mining Corp. [2006-10-03]: Press Release - Merit Updates Greenwood Gold Project Resource Base
GOLDEN CROWN 2004 Y	30,700 t Indicated	Gold Copper	17.9 g/t 0.8 %	At a cut-off of six grams per tonne gold equivalent. News Release, Gold City Industries Ltd., May 17, 2004
GOLDEN CROWN 2004 Y	74,200 t Inferred	Gold Copper	12.7 g/t 0.6 %	At a cut-off of six grams per tonne gold equivalent. News Release, Gold City Industries Ltd., May 17, 2004
DRILLHOLE 2003 N	Assay/analysis Drill Core	Gold Copper	362.82 g/t 0.39 %	Drill intercepts on the veins yielded up to 362.82 grams per tonne gold with 0.39 per cent copper over 1.86 metres in hole 03CDH-01 and 72.14 grams per tonne gold with 1.31 per cent copper over 1.25 metre in hole 03CDH-03, both on the King vein; 21.73 grams per tonne gold with 0.41 per cent copper over 0.94 metres on the Samaritan vein; 81.20 grams per tonne gold with 0.24 per cent copper over 1 metre from the Tiara vein, 1.85 grams per tonne gold over 1.95 metres from the Golden Crown (Portal) vein and 1.41 grams per tonne gold over 2.74 metres from the Calumet vein Property File - D. Terry [2003-12-05]: Weekly Reports - Kootenay Region - Golden Crown

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN		33,740 t	Gold	18.38 g/t	In 1990, Attwood undertook a program of surface drilling (34 holes), geochemistry, geophysics, as well as surveying all identifiable drill hole collars. An independent reserve estimate was completed, and reserves were estimated at 33,740 tonnes at an average grade of 18.38 grams per tonne gold (cut), 34.29 grams per tonne gold (uncut) and 1 per cent copper (as reported in Assessment Report 25895). The discrepancy between this and previous estimates was deemed to be largely the result of inaccurate drill hole locations. Assessment Report 25895
1990	N	Unclassified	Copper	1 %	
MAIN		56,850 t	Gold	15.26 g/t	an estimated drill indicated resource was made of 56,850 tonnes averaging 15.26 grams per tonne gold, 17.83 grams per tonne silver and 0.70 per cent copper Property File - Attwood Gold Corporation [1989-06-29]: Filing Statement #69/89
1989	N	Indicated	Silver Copper	17.83 g/t 0.70 %	
DRILLHOLE			Gold	492.5 g/t	drill hole GCU 89-5A intercepted a zone of massive sulphides 30 metres below the main drift level yielding 492.5 grams per tonne gold over 4.5 metres Property File - Attwood Gold Corporation [1989-06-29]: Filing Statement #69/89
1989	N	Assay/analysis Drill Core			
MAIN			Gold	23.9 g/t	Two 22.7 kilogram bulk samples from a cross-cut yielded an average of 23.9 grams per tonne gold Property File - GCNL [1988-04-27]: No. 81 (1988) - Golden Crown, Reliance, Giant Copper, Dragon Creek
1988	N	Assay/analysis Bulk Sample			
DRILLHOLE			Gold	141.6 g/t	diamond drilling on the King and George veins established the continuity of the veins to 60 metres below the main shaft with intercepts yielding up to 141.6 grams per tonne gold, 27.0 grams per tonne silver and 0.71 per cent copper over 1.62 metres in hole 88-1; 44.8 grams per tonne gold, 37.6 grams per tonne silver and 2.85 per cent copper over 0.48 metre in hole 88-16; 35.2 grams per tonne gold, 45.1 grams per tonne silver and 0.29 per cent copper over 2.37 metres in hole 88-18; 42.8 grams per tonne gold and 0.55 per cent copper over 0.6 metre in hole 88-23; 213.1 grams per tonne gold and 0.45 per cent copper over 9 centimetres in hole 88-26 and 492.5 grams per tonne gold over 4.5 metres in hole 89-5A Property File - GCNL [1988-07-25]: No. 142 (1988) - Lara, Indian, Katanga, Golden Crown, Brett, SNIP; GCNL [1989-02-16]: No. 33 (1989) - Golden Crown, Snowbird
1988	N	Assay/analysis Drill Core	Silver Copper	27.0 g/t 0.71 %	
UNDERGROUND			Gold	25.3 g/t	underground sampling, yielded up to 25.3 grams per tonne gold across 0.9 metre along a mineralized structure followed for 15 metres near the portal, 3.4 to 23.9 grams per tonne gold across 0.69 metre of massive sulphide vein from 45 to 92.1 metres of a drift and 5.8 grams per tonne gold across 0.96 metre of serpentine contact exposed in a drift Property File - Consolidated Boundary Explorations Ltd. [1987-11-16]: News - Exploration - Golden Crown property
1987	N	Assay/analysis Chip			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Gold	43.1 g/t	drilling on a parallel zone, located 300 metres south of the main zone, yielded up to 43.1 grams per tonne gold over 1.3 metres in hole 86-2 and 7.8 grams per tonne gold over 1.4 metres in hole 86-3 Property File - Consolidated Boundary Exploration Ltd. [1986-11-12]: News - Exploration - Golden Crown property
1986	N	Assay/analysis Drill Core			
DRILLHOLE			Gold	10.7 g/t	drilling on the northwest zone yielded up to 10.7 grams per tonne gold over 1.2 metres of massive sulphides Property File - Consolidated Boundary Exploration Ltd. [1986-06-11]: Deal On Gold Prospect In B.C. Is Imminent
1985	N	Assay/analysis Drill Core			
DRILLHOLE			Gold	30.2 g/t	drilling extended the main zone down dip for an additional 42 metres to a total depth of 132 metres with intercepts yielded up to 17.3 grams per tonne gold and 0.63 per cent copper over 3.0 metres in hole 84-26, while other holes intercepted a 'new' parallel zone, to the south, yielding up to 30.2 grams per tonne gold, 17.1 grams per tonne silver and 0.61 per cent copper over 0.6 metre in hole 84-24 and 10.6 grams per tonne gold, 39.0 grams per tonne silver and 2.38 per cent copper over 1.44 metres in hole 84-22 Property File - Consolidated Boundary Exploration Ltd. [1985-03-01]: Further Drilling Planned For 1985
		Assay/analysis	Silver	17.1 g/t	
1984	N	Drill Core	Copper	0.61 %	
DRILLHOLE			Gold	23.4 g/t	drilling intercepted two mineralized zones in hole 83-18 yielding 11.8 grams per tonne gold, 81.4 grams per tonne silver with 3.45 per cent copper over 2.22 metres at a depth of 62.4 metres and 23.4 grams per tonne gold, 56.8 grams per tonne silver with 3.63 per cent copper over 1.26 metres at a depth of 109.2 metres Property File - Consolidated Boundary Exploration [1984-03-01]: News - 1983 drilling - Golden Crown - Phoenix property
		Assay/analysis	Silver	56.8 g/t	
1983	N	Drill Core	Copper	3.63 %	
DRILLHOLE			Gold	46.2 g/t	Two drill holes (79-2 and 79-3), located south east and east of the Golden Crown shaft, yielded 25.0 and 46.2 grams per tonne gold, 10.3 and 13.7 grams per tonne silver with 1.03 and 0.30 per cent copper over 0.96 and 0.45 metre, respectively Property File - Consolidated Boundary Exploration Ltd. [1979-11-29]: News Clipping - Two Further Holes Yield Good Assay Results
		Assay/analysis	Silver	13.7 g/t	
1979	N	Drill Core	Copper	0.30 %	
DRILLHOLE			Gold	8.2 g/t	Two drill holes (G.C. Nos. 9 and 11), located south east of the Golden Crown shaft and north east of the MacArthur shaft, yielded incepts of 8.2 grams per tonne gold with 0.33 per cent copper over a true width of 2.1 metres and 6.8 grams per tonne gold with 0.40 per cent copper over a true width of 1.35 metres, respectively Property File - Con-Am Resources Ltd. [1978-12-12]: News Clipping - Drilling and exploration - Golden Crown property
		Assay/analysis	Copper	0.33 %	
1977	N	Drill Core			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1967	N	Assay/analysis Drill Core	Gold	13.0 g/t	Drill hole S-3 intercepted 13.0 grams per tonne gold, 43.1 grams per tonne silver and 1.01 per cent copper over 1.5 metres Property File - CON-AM Resources Ltd. [1977-10-31]: Report on the Golden Crown Group
			Silver	43.1 g/t	
			Copper	1.01 %	