

<b>MINFILE Number:</b>	082FNW154	<b>Name:</b>	ANNA (L.14468)	<b>Status:</b>	Past Producer
------------------------	-----------	--------------	----------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
EAST			Silver	17.1 g/t	sampling of the 'East' vein yielded up to 17.1 grams per tonne silver over 0.9 metre
1967	N	Assay/analysis Chip			Property File - M.K. Lorimar [1967-12-11]: Report on the Anna, Myrtle, Mulvey Creek and Flathead Properties
WEST			Silver	6902 g/t	a sample (no.639) of the 'West' vein from a stope on the no.3 level assayed 6902 grams per tonne silver over 0.3 metre
1967	N	Assay/analysis Chip			Property File - M.K. Lorimar [1967-12-11]: Report on the Anna, Myrtle, Mulvey Creek and Flathead Properties
WEST			Silver	3670 g/t	eight samples from the 'West' or footwall vein yielded an average of 1.7 grams per tonne gold and 3670 grams per tonne silver over an average width of 0.84 metre
1927	N	Assay/analysis Chip	Gold	1.7 g/t	Property File - M.K. Lorimar [1969-04-08]: Report on the Anna Mine