

MINFILE Number:	082FSW001	Name:	ASPEN (L.12471)	Status:	Past Producer
------------------------	-----------	--------------	-----------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2008	N	Assay/analysis Grab	Silver	249 g/t	Sample AP080-05. EMPR ASS RPT 30317
			Gold	1.1 g/t	
			Lead	11.96 %	
			Zinc	0.55 %	
1999	N	Assay/analysis Chip	Zinc	12.5 %	Sample 645-RK002 taken over 2.5 metres. EMPR ASS RPT 26135
1981	Y	49,120 t Measured	Silver	235.0000 g/t	Proven reserves of silver zone, average thickness of 3.4 metres; with minor lead and zinc (Quadros, 1981). Also 12,180 tonnes of indicated of similar grade material. Taylor, 1984.
1980	N	Assay/analysis Drill Core	Silver	246.8500 g/t	Weighted average of diamond-drill hole U80-02. Assessment Report 9053.
			Gold	2.4000 g/t	
			Lead	0.3900 %	
			Zinc	3.9500 %	
1959	Y	36,287 t Indicated	Zinc	3.1600 %	Cominco's work. Taylor, 1984.