

MINFILE Number:	082KNW039	Name:	SILVER CHIEF	Status:	Prospect
------------------------	-----------	--------------	--------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
LOWER			Silver	77.0 g/t	three chip samples (601F through 603F) from the no. 6 (Lower) zone yielded 77.0, 17.1 and 30.8 grams per tonne silver with 19.60, 14.70 and 4.40 per cent lead over 0.45, 2.52 and 2.58 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property
1977	N	Assay/analysis Chip	Lead	19.60 %	
WEST			Silver	34.2 g/t	Two other chip samples (604F and 605F), taken 225 metres west and 120 metres above the adit, assayed 34.2 and 10.3 grams per tonne silver with 4.95 and 1.45 per cent lead over 1.38 and 1.08 metres, respectively Property File - Tacoma Resources Ltd. [1977-04-28]: Geological Report on the Silver Chief Property
1977	N	Assay/analysis Chip	Lead	4.95 %	
LOWER			Lead	41.89 %	Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims
1970	N	Assay/analysis Grab	Silver	179.9 g/t	
NO. 5			Lead	64.02 %	Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims
1970	N	Assay/analysis Grab	Silver	385.8 g/t	
NO. 5			Silver	96.0000 g/t	across 1.0 metre of the no. 5 (Upper) zone Ministry of Energy, Mines and Petroleum Res. Bulletin 45, page 74.
1962	N	Assay/analysis Chip	Lead	16.1600 %	
NO. 5			Silver	94.3000 g/t	Sample collected over 1.22 metres. EMPR ASS RPT 360
			Gold	0.5100 g/t	
1960	N	Assay/analysis Chip	Lead	16.7000 %	
NO. 4			Silver	167.6 g/t	a sample from the no. 4 zone assayed 167.6 grams per tonne silver and 26.29 per cent lead across 38 centimetres Property File - A.G. Mackenzie [1971-04-01]: Geological Report on the Silver Chief Claims
1960	N	Assay/analysis Chip	Lead	26.29 %	