MINFILE Number: 082LNW031 **Name:** FS **Status:** Past Producer

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT 2015 N	Assay/analysis Grab	Silver Lead	758 g/t 3.10 %	grab samples (M-4) across 1.5 metres Assessment Report 36150
PIT 1996 N	Assay/analysis Channel	Lead Zinc Silver	1.7 % 0.08 % 377.2 g/t	average of three channel samples (S-2, S-4, S-6) over 3.51 metres Assessment Report 25115
PIT 1996 N	Assay/analysis Drill Core	Silver	9.1 g/t	a quartz zone hosting 5 to 15 per cent sulphides over 35.25 metres. A 3.0 metre section, near the end of the zone, assayed 9.1 grams per tonne Assessment Report 25115
PIT 1981 N	Assay/analysis Drill Core	Lead Zinc Silver	1.49 % 1.6 % 520.2 g/t	In 1981, diamond drilling (hole S-80-5) yielded values up to 520.2 grams per tonne silver, 1.49 per cent lead and 1.60 per cent zinc over 1.8 metres; while a 10.2 metre section averaged 116.3 grams per tonne silver, 0.164 per cent zinc and 0.156 per cent lead Assessment Report 9529
SAMPLE 1969 N	Assay/analysis Chip	Silica	46.6000 %	Random sample from northern exposure. Also analysed 0.064 per cent total Fe, trace Al2O3 and nil CaO. Open File 1987-15, page 29.