

MINFILE Number:	082LSE017	Name:	TOP	Status:	Prospect
------------------------	-----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH			Gold	16.8 g/t	Sampling of a new trench is reported to have yielded 16.8 grams per tonne gold over 12.5 metres.
2003	N	Assay/analysis Rock			Assessment Report 29324
TRENCH			Gold Silver	22.55 g/t 12 g/t	A sample (TOP99-07) of pyritic rock from the shear zone exposed in the historic Trench 2 assayed 22.55 grams per tonne gold and 12 grams per tonne silver, while a sample (TOP99-01) of dump material from the decline shaft/adit yielded 10.24 grams per tonne gold and 5.8 grams per tonne silver.
1999	N	Assay/analysis Rock			Assessment Report 263494
WORKINGS			Gold	14.1 g/t	Sampling at the base of the 126.5 metre decline over 9 metres.
1990	N	Assay/analysis Chip			Assessment Report 21656
DRILLHOLE			Gold	15.0000 g/t	Sample of sheared and altered dike, over 14 metres.
1988		Assay/analysis Drill Core			Assessment Report 18426.