

<b>MINFILE Number:</b>	082LSW042	<b>Name:</b>	WHITE ELEPHANT (L. 4880)	<b>Status:</b>	Past Producer
------------------------	-----------	--------------	--------------------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP			Gold	35.6 g/t	grab samples from a dump pile
1988	N	Assay/analysis Grab	Silver	27.0 g/t	Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
MAIN			Gold	51.98 g/t	a 1.0 metre chip sample (31839) from a quartz body containing a 0.5 metre sulphide bleb
1988	N	Assay/analysis Chip	Silver Bismuth	10.9 g/t 0.136 %	Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization
TRENCH			Gold	8.6 g/t	average of samples from a trench on the upper most mine dump
1980	N	Assay/analysis Grab	Silver	17.8 g/t	Property File – E.J. Kondra [1980-02-29]: Letters Re: Mineral Claims, Crown Granted Mineral Claims, Vernon Area
UNDERGROUND			Gold	12.7 g/t	Prior to closing, in 1935, underground development on the 300-foot level is reported to have averaged 12.7 grams per tonne gold over 2.1 metres
1935	N	Assay/analysis Chip			Property File - C.J. Sampson [1988-06-30]: Prospectus: Lucky 7 Exploration Ltd., Report on the Geology, Geochemical Soil Sampling, VLF E.M., Magnetometer, Induced Polarization