

MINFILE Number:	082M 125	Name:	COMPLEX	Status:	Developed Prospect
------------------------	----------	--------------	---------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
B			Lead	19.96 %	four samples (545640 through 545643) for the area of the Bass shaft yielded values from 4.48 to 19.96 per cent lead, 0.05 to 0.57 per cent zinc and 48 to 171 grams per tonne silver Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property
		Assay/analysis	Zinc	0.57 %	
2011	N	Rock	Silver	171 g/t	
OUTCROP			Silver	97.0000 g/t	Average of 21 surface chip samples across 1.4 metres along zone. Property File (Report by A.R. Allen, 1966).
		Assay/analysis	Lead	5.3700 %	
1966		Chip	Zinc	6.5100 %	
B			Lead	2.80 %	a sample taken south east of the Bass shaft over 76.2 centimetres Williams, J.D. (2012-06-12): Technical Report on the Copper King – Cotton Belt Property
		Assay/analysis	Zinc	2.50 %	
1951	N	Chip	Silver	68.6 g/t	