

MINFILE Number:	082N 004	Name:	WOOLSEY	Status:	Past Producer
------------------------	----------	--------------	---------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP			Lead	1.51 %	four dump samples from the no. 8, 9 and 10 levels yielded from 0.08 to 1.51 per cent lead, trace to 1.33 per cent zinc, trace to 0.03 per cent tungsten and 5.5 to 46.6 grams per tonne silver Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
		Assay/analysis	Zinc	1.33 %	
1987	N	Grab	Tungsten	0.03 %	
			Silver	46.6 g/t	
TOTAL		590,703 t	Silver	71.6000 g/t	Reported reserves. Prospectus, Gunsteel Resources Inc., April 29, 1986.
		Unclassified	Copper	1.1000 %	
1982	Y		Lead	2.6600 %	
			Tin	0.1300 %	
			Tungsten	0.0150 %	
			Zinc	1.2600 %	
DRILLHOLE			Zinc	18 %	diamond drilling yielded up to 18 per cent zinc over 0.3 metre and 0.52 per cent tungsten over 0.05 metre in hole RS-82-2, located to the north east on Clabon Creek Assessment Report 8963
		Assay/analysis	Tungsten	0.52 %	
1980	N	Drill Core			
MAIN		658,616 t	Silver	90.3 g/t	This was revised in 1971, after further underground sampling, for reserve of 658,616 tonnes grading 90.3 grams per tonne silver, 2.55 per cent lead and 1.15 per cent zinc with an additional block of 16,964 tonnes grading 1.05 per cent tungsten trio-oxide Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
		Unclassified	Lead	2.55 %	
1971	N		Zinc	1.15 %	
MAIN		590,758 t	Silver	92.0 g/t	an estimate of proven and probable reserves of 590,758 tonnes grading 92.0 grams per tonne silver, 2.66 per cent lead, 1.26 per cent zinc, 1.10 per cent copper, 0.13 per cent tin, 0.02 per cent cadmium and 0.02 per cent tungsten tri-oxide was reported, including a block of 25,129 tonnes grading 1.31 per cent tungsten tri-oxide Property File - Albar Resources Ltd. [1989-04-28]: Prospectus Report - Regal Silver Property
		Unclassified	Lead	2.66 %	
1969	N		Zinc	1.26 %	
			Copper	1.10 %	
			Tin	0.13 %	
			Tungsten	0.02 %	
			Cadmium	0.02 %	
NO. 4			Silver	78.7 g/t	underground sampling of the workings adjoining the no. 4 level of the Snowflake (MINFILE 082N 003) mine but on the Regal Silver property, yielded an average of 78.7 grams per tonne silver, 0.20 per cent lead, 2.28 per cent zinc and 0.35 per cent tin over a length of 31.8 metres and a width of 0.51 metre Property File - C.S. Lord [1942-12-01]: Assay Plan Map - Part of Snowflake Level
		Assay/analysis	Lead	0.20 %	
1942	N	Chip	Zinc	2.28 %	
			Tin	0.35 %	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1942	N	Assay/analysis Drill Core	Tin	0.15 %	underground diamond drilling yielded: 0.62 per cent tin, 0.95 per cent lead and 0.41 per cent zinc over 48 centimetres in hole no. 1; 0.15 per cent tin, 1.28 per cent lead and 0.35 per cent zinc over 1.6 metres in hole no. 2 and 0.08 per cent tin, 0.86 per cent lead with 1.97 per cent zinc over 1.11 metres in hole no. 3; 0.36 per cent time over 12 centimetres in hole no. 4. Silver values were not reported. Property File - C.S. Lord [1943-02-26]: Diamond Drilling and Sampling at Regal Silver and Snowflake Properties
			Lead	1.28 %	
			Zinc	0.35 %	
1930	N	Assay/analysis Chip	Silver	171.0 g/t	sampling of the no. 5 vein from the no. 2 tunnel yielded an average of 171.0 grams per tonne silver, 5.0 per cent lead, 1.2 per cent zinc with 0.1 per cent tin over a length of 105 metres and a width of 4.5 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
			Lead	5.0 %	
			Zinc	1.2 %	
			Tin	0.1 %	
1930	N	Assay/analysis Chip	Silver	102.6 g/t	Sampling of the no. 6 vein from the no. 3 level yielded an average of 102.6 grams per tonne silver, 1.5 per cent lead, 0.9 per cent zinc and 0.5 per cent tin over a length of 157.5 metres and a width of 2.4 metres, with individual samples yielding up to 2.9 per cent tin Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
			Lead	1.5 %	
			Zinc	0.9 %	
			Tungsten	0.5 %	
1930	N	Assay/analysis Chip	Silver	229.1 g/t	sampling of the no. 5 vein from the no. 3 level averaged 229.1 grams per tonne silver, 6.1 per cent lead, 1.8 per cent zinc and 0.5 per cent tin over a length of 72 metres and a width of 1.95 metres Property File - F.W. Guernsey [1930-11-30]: Report - Regal Silver Mines Limited - 19 Mineral Claims
			Lead	6.1 %	
			Zinc	1.8 %	
			Tin	0.5 %	