

<b>MINFILE Number:</b>	092C 007	<b>Name:</b>	MONITOR	<b>Status:</b>	Past Producer
------------------------	----------	--------------	---------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2009	N	Assay/analysis Grab	Copper	1.02 %	sample (200914), taken approximately 100 metres to the east of the shaft, from a 0.2 metre thick exposure of pyritic quartz containing chlorite, jarosite, chalcopyrite and hematite assayed 1.02 per cent copper, 45.6 grams per tonne silver and greater than 1 per cent lead and zinc Assessment Report 31248
			Zinc	1 %	
			Lead	1 %	
			Silver	45.6 g/t	
2009	N	Assay/analysis Grab	Copper	3.41 %	a select grab sample (2009012) from a 0.2 metre thick exposure of skarn in the shaft Assessment Report 31248
			Lead	0.223 %	
			Silver	58.2 g/t	
			Zinc	1 %	
2009	N	Assay/analysis Grab	Copper	5 %	two grab samples, 362676 and 362677, of oxidized skarn from a former trench assayed 0.68 and 5.0 per cent copper, 3.7 and 0.13 per cent zinc with 12 and 23 grams per tonne silver, respectively Assessment Report 29660
			Silver	23 g/t	
			Zinc	3.7 %	
1919	N	Assay/analysis Chip	Silver	17.1400 g/t	0.6 metre sample. Minister of Mines Annual Report 1919, page 253.
			Copper	6.1000 %	