

| MINFILE Number: | 092E 002 | Name: BEA | ANO | Status: Past Producer |
|-----------------------------|------------------------------|----------------|---------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
| OPENCUT 1989 N | Assay/analysis Grab | Gold | 53.1 g/t | average of nine samples from the No. 5 and 6 trenches Assessment Report 19677 |
| OPENCUT 1989 N | Assay/analysis Chip | Gold | 17.7 g/t | sampling of the No. 4 trench over 2.7 metres Assessment Report 19677 |
| OUTCROP 1989 N | Assay/analysis Chip | Gold | 47.3 g/t | over 7.5 metres, including 70.8 grams per tonne gold over 5.0 metres from a zone exposed along the creek canyon Assessment Report 19677 |
| SAMPLE 1989 N | Assay/analysis Rock | Gold Copper | 1.02 g/t 0.381 % | Sample BC-630, located approximately 300 metres down slope and to the south- southeast of the main trenched zone and from the southeastern (mapped) extent of the same limestone host unit as the main Beano zone. Assessment Report 19677 |
| SAMPLE 1989 N | Assay/analysis Rock | Gold | 3.3 g/t | Another rock sample (BC-757) taken from an area of andesitic volcanics exposed along a logging road approximately 1.1 kilometres to the south of the main Beano zone and at an elevation of approximately 340 meters Assessment Report 19677 |
| DRILLHOLE 1983 N | Assay/analysis Drill Core | Gold | 13.6 g/t | over 3.2 metres in hole DD3 Assessment Report 12573 |
| DRILLHOLE 1983 N | Assay/analysis Drill Core | Gold | 19.7 g/t | over 2.6 metres in hole DD4 Assessment Report 12573 |
| DRILLHOLE 1983 N | Assay/analysis Drill Core | Gold | 14.3 g/t | over 1.9 metres in hole DD5 Assessment Report 12573 |
| DRILLHOLE 1983 N | Assay/analysis Drill Core | Gold | 21.7 g/t | over 1.0 metre in hole DD6 Assessment Report 12573 |

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---------------------------|----------------|----------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| OPENCUT 1981 N | Assay/analysis Chip | Gold Copper | 83.4 g/t 0.23 % | a chip sample (ZEB-4) from the No. 4 cut, located at an elevation of 796 metres Assessment Report 9981 |
| STOCKPILE 1981 N | Assay/analysis Grab | Gold Copper | 67.7 g/t 0.11 % | A sample (ZEB-3) from a ore stockpile Assessment Report 9981 |
| OUTCROP 1972 N | Assay/analysis Chip | Gold | 20.5 g/t | over 8.7 metres Property File - J.D. Mason [1973-09-10]: New Taku Mines Ltd 1972 Annual Report |
| ADIT 1972 N | Assay/analysis Chip | Gold | 48.6 g/t | over 0.6 metre of massive pyrrhotite (sample 1862) from the north adit Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano |
| ADIT 1972 N | Assay/analysis Chip | Gold | 46.5 g/t | over 1.8 metres (sample 1863) from the north face of the south adit Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano |
| OPENCUT 1972 N | Assay/analysis Chip | Gold | 148.8 g/t | sample 1854 over 1.8 metres from the No. 1 open cut Property File - New Taku Mines Ltd. [1972-08-22]: Sample Descriptions, Assays and Sketch Map - Beano |
| OPENCUT 1946 N | Assay/analysis Grab | Gold | 154.6 g/t | sampling of a 'lower' open cut over 2.7 metres Property File - E. Crowe (1941-07-15): Report on the Beano Group of Mining Claims; W.A. Lammers [1946-07-04]: Report - Beano Group |
| OPENCUT 1941 N | Assay/analysis Channel | Gold | 98.5 g/t | channel samples (No.3) over 3.38 metres from open cut No. 1 Property File - E. Crowe [1941-07-15]: Report on the Beano Group of Mining Claims |
| OPENCUT 1939 N | Assay/analysis Grab | Gold | 62.6 g/t | grab samples taken across 5.1 metres of an open cut Property File - H.G. Lynch [1939-04-27]: Letter Re: Preliminary Examination of the Beano property |
| OPENCUT 1938 N | Assay/analysis Grab | Silver Gold | 6.8000 g/t 321.7000 g/t | Massive pyrrhotite, Number 4 Cut. Minister of Mines Bulletin 27, page 138. |