

<b>MINFILE Number:</b>	092F 029	<b>Name:</b>	TOFINO NICKEL	<b>Status:</b>	Prospect
------------------------	----------	--------------	---------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2000	N	Assay/analysis Chip	Copper	3.4 %	Two trenches, adjacent to the main showing, were tested and yielded 3.4 and 3.1 per cent copper, 0.7 and 2.1 per cent nickel, 2.4 and 1.6 grams per tonne platinum with 8.3 and 4.8 grams per tonne palladium over 2.7 and 2.5 metres. Assessment Report 26481
			Nickel	2.1 %	
			Platinum	2.4 g/t	
			Palladium	8.3 g/t	
1997	N	Assay/analysis Grab	Copper	2.58 %	In 1997, Arnex Resources Ltd. completed a geology and rock chip sampling program at the main showing area. This work extended the massive sulphide zone to the southeast with a sample (437740) yielding 2.58 per cent copper, greater than 1.0 per cent zinc, 0.232 grams per tonne gold, 1.89 grams per tonne platinum and 6.42 grams per tonne palladium over 0.5 metre. Assessment Report 25108
			Zinc	1 %	
			Gold	0.232 g/t	
			Platinum	1.89 g/t	
1997	N	Assay/analysis Chip	Palladium	6.42 g/t	
			Gold	0.204 g/t	A representative chip sample (437736) of disseminated mineralization over 10 metres yielded values of 0.498 per cent copper, 0.051 per cent nickel and 0.204 gram per tonne gold. Assessment Report 25108
			Copper	0.498 %	
			Nickel	0.051 %	
1994	N	Assay/analysis Chip	Nickel	2.06 %	In 1994, a 2.2-metre rock chip channel sample on the area previously sampled by Cominco, in 1985. Assessment Report 23283
			Copper	1.97 %	
			Platinum	1.75 g/t	
			Palladium	5.87 g/t	
1988	N	Assay/analysis Grab	Gold	1.1000 g/t	Another sample assayed 48.0 grams per tonne silver (Minister of Mines Annual Report 1963, page 116). Assessment Report 17284.
			Copper	18.6000 %	
			Nickel	15.0000 %	
			Palladium	18.7000 g/t	
1985	N	Assay/analysis Chip	Platinum	6.9000 g/t	
			Copper	4.2 %	A chip sample over 11.1 metres. Assessment Report 23283
			Platinum	1.4 g/t	
			Palladium	4 g/t	
1963	N	Assay/analysis Grab	Zinc	1.5 %	
			Silver	48 g/t	Minister of Mines Annual Report 1963, page 116