

<b>MINFILE Number:</b>	092GNW014	<b>Name:</b>	BELLE	<b>Status:</b>	Showing
------------------------	-----------	--------------	-------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
CREEK			Copper	15.7 %	Sampling of the type 1 style of mineralization from the creek canyon yielded up to 15.7 per cent copper and 109.1 grams per tonne silver over 0.5 metre Assessment Report 11121
1983	N	Assay/analysis Chip	Silver	109.1 g/t	
SOUTHEAST			Copper	1.0 %	sampling of the south eastern mineralized exposures, of type 3 mineralization yielded 0.5 to 1.0 per cent copper, 3.26 to 7.06 per cent zinc and 0.17 to 1.09 per cent lead Assessment Report 11121
1983	N	Assay/analysis Rock	Zinc	7.06 %	
			Lead	1.09 %	
WEST			Copper	17.3 %	Sampling of the other mineralized exposures to the west, of type 1 mineralization, yielded averages from 2.5 to 7 per cent copper and up to 17.3 per cent copper, 112.2 grams per tonne silver and 2.1 grams per tonne gold over 0.1 metre Assessment Report 11121
1983	N	Assay/analysis Rock	Silver	112.2 g/t	
			Gold	2.1 g/t	