

MINFILE Number:	092HNE086	Name:	TOM CAT (L.1517)	Status:	Prospect
------------------------	-----------	--------------	------------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Copper	0.54 %	A single drill hole (K07-03) confirmed the historic results intersecting a 41.1 metre (20.4 to 61.5 metres down-hole) mineralized section, including 0.54 per cent copper over 5.6 metres (20.4 to 26.0 metres down-hole). Assessment Report 29728
2007	N	Assay/analysis Drill Core			
SAMPLE			Copper	1.77 %	Chip sample (K-03), taken from a mineralized pod exposed 20 metres west of the trench. Assessment Report 28782
2006	N	Assay/analysis Chip	Silver	9.2 g/t	
TRENCH			Copper	3.68 %	A chip sample (K-02) over 2 metres of the face of a historic trench. Assessment Report 28782
2006	N	Assay/analysis Chip	Silver	9.8 g/t	
LAKE			Copper	0.728 %	A grab sample (28339) of angular sub-crop comprising calcareous volcanic sediment or limestone with limonite staining and pyrite, bornite, azurite and malachite mineralization located southwest of a small lake, approximately 400 metres northeast of the Tom Cat occurrence. The sample also yielded 0.093 per cent antimony. Assessment Report 25158
1997	N	Assay/analysis Grab	Silver	14.3 g/t	
LAKE			Silver	6.2 g/t	Two samples (6708 and 6707), taken west of a small lake and approximately 450 metres north of the Tom Cat occurrence, yielded 0.695 and 0.517 per cent copper with 3.1 and 6.2 grams per tonne silver, respectively. Assessment Report 17118
1987	N	Assay/analysis Rock	Copper	0.695 %	
SAMPLE			Copper	1.294 %	A sample (6849) from the Tom Cat occurrence area. Assessment Report 17118
1987	N	Assay/analysis Rock	Silver	2.8 g/t	
LAKE			Copper	1.277 %	Three rock samples (B-2069, B-2071 and 2249) from the area southwest of a small lake to the northeast of the occurrence yielded from 0.381 to 1.277 per cent copper and 0.7 to 3.4 grams per tonne silver. Assessment Report 14141
1985	N	Assay/analysis Rock	Silver	3.4 g/t	
DRILLHOLE			Copper	0.3150 %	Average grade over 45.7 metres. Minister of Mines Annual Report 1965, page 157 (hole 1, 0 to 45.7 m).
1965	N	Assay/analysis Drill Core			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH		Assay/analysis Chip	Copper	1.6000 %	Chip sample taken over a length of 3.0 metres. Minister of Mines Annual Report 1913, page 223.
1913	N				