

MINFILE Number: 092HNE088	Name: PORTLAND (L.1124)	Status: Showing
----------------------------------	--------------------------------	------------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP			Copper	0.170 %	Shaft dump sample K-06. Assessment Report 28782
2006	N	Assay/analysis Grab			
DUMP			Copper Silver	1.125 % 5.0 g/t	Four composite grab samples (28347 through 28350) of waste and ore dump material from the Portland shaft yielded from 0.311 to 1.125 per cent copper with 1.6 to 5.0 grams per tonne silver. Assessment Report 25158
1997	N	Assay/analysis Grab			
OUTCROP			Copper	0.362 %	Two grab samples (28345 and 38246) of carbonate, chlorite and hematite altered andesitic volcanics hosting malachite yielded 0.166 and 0.362 per cent copper, respectively. Assessment Report 25158
1997	N	Assay/analysis Grab			
OUTCROP			Copper Silver	1.52 % 6.8 g/t	A composite grab sample (28501) of andesite to basalt with quartz+/-carbonate stringers and malachite. Assessment Report 24522
1996	N	Assay/analysis Grab			
OUTCROP			Copper	0.34 %	Chip sample (28502) of andesite to basalt with quartz+/-carbonate stringers and malachite over 4.5 metres. Assessment Report 24522
1996	N	Assay/analysis Chip			
OUTCROP			Copper	0.97 %	A composite grab sample (28509) of silicified and malachite-stained andesite to basalt, taken to the northwest of the shaft. Assessment Report 24522
1996	N	Assay/analysis Grab			
DUMP			Copper	0.75 %	A composite sample (28506) of dump material adjacent to the Portland shaft. Assessment Report 24522
1996	N	Assay/analysis Grab			
DUMP			Copper	0.4000 %	Minister of Mines Annual Report 1913, page 223.
1913		Assay/analysis Grab			
OPENCUT			Copper	0.9 %	A sample from an open cut. Minister of Mines Annual Report 1901, page 1183
1901	N	Assay/analysis Rock			