

<b>MINFILE Number:</b>	092ISE027	<b>Name:</b>	LUCKY MIKE	<b>Status:</b>	Past Producer
------------------------	-----------	--------------	------------	----------------	---------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE		Tungsten	0.17 %	Drilling on the Luck Mike occurrence yielded intercepts including 0.15 per cent tungsten over 20 metres in hole LM-2, 0.17 per cent copper, 26.4 grams per tonne silver and 0.12 per cent tungsten over 9 metres in hole LM-3 and 0.17 per cent tungsten over 23.9 metres in hole LM-4, while another drill hole (LM-7) located several hundred metres north of the previous holes yielded 0.22 per cent zinc over 42.08 metres, including 0.2 per cent copper, 0.08 per cent tungsten with 8.6 grams per tonne silver over 24.83 metres Assessment Report 35480
2014 N	Assay/analysis Drill Core			
TRENCH		Copper	3.537 %	a 1.0 metre chip sample (80964)
		Silver	82.5 g/t	Turner, J.A. (2012-09-17): Technical Report NI 43-101
2011 N	Assay/analysis Chip	Tungsten	0.41 %	for the Lucky Mike Copper-Tungsten Property
DRILLHOLE		Copper	0.25 %	0.25 per cent copper, 8.7 grams per tonne silver and
		Silver	8.7 g/t	0.26 gram per tonne gold over 2.5 metres and 5.41 per
1993 N	Assay/analysis Drill Core	Gold	0.26 g/t	cent copper, 160.4 grams per tonne silver and 0.60 gram per tonne gold over 0.24 metre in hole 93-7 located on a magnetic anomaly Turner, J.A. (2013-03-14): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property
DRILLHOLE		Silver	38.3900 g/t	Tungsten assay across 14.1 metres of mineralized skarn.
		Copper	0.1800 %	Copper and silver assays are across 3.6 metres of
1988	Assay/analysis Drill Core	Tungsten	0.1520 %	mineralized skarn. Assessment Report 18583.
TOTAL	317,485 t	Silver	20.5000 g/t	Estimated geologic reserves.
	Indicated	Copper	0.5600 %	Assessment Report 24600, page iii.
1973 Y		Tungsten	0.2300 %	
TRENCH		Tungsten	0.25 %	tungsten tri-oxide over a width of 10.2 metres
				(Turner, J.A. (2012-09-17): Technical Report NI
1943 N	Assay/analysis Chip			43-101 for the Lucky Mike Copper-Tungsten Property
DRILLHOLE		Tungsten	0.312 %	tungsten tri-oxide in eight holes over an average width of
				7.5 metres
1943 N	Assay/analysis Drill Core			Turner, J.A. (2012-09-17): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property