MINFILE Number: 093F 103 **Name:** LIESEGANG **Status:** Showing

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT 2017	N	Assay/analysis Grab	Copper Silver	2.811 % 7.047 g/t	A grab sample from the boulder yielded 2.811 per cent Cu and 7.047 grams per tonne Ag (Geoscience BC Report 2016-1). Geoscience BC Report 2016-1
SAMPLE 2017	N	Assay/analysis Rock	Copper Silver	2.79 % 9.0 g/t	rock sample L017056 Assessment Report 36886
FLOAT 2016	N	Assay/analysis Grab	Copper Silver	3.008 % 8.6 g/t	Two float samples (2575012 and 2575013) of quartz-epidote+/-calcite veined basalt with native copper from the Liesegang occurrence yielded 2.747 and 3.008 per cent copper with 7.2 and 8.6 grams per tonne silver, respectively Assessment report 36473