

<b>MINFILE Number:</b> 093J 037	<b>Name:</b> PM	<b>Status:</b> Showing
---------------------------------	-----------------	------------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1996	N	Assay/analysis	Gold	0.101 g/t	disseminated pyrite mineralization in Takla Group volcanics yielded up to 0.101 gram per tonne gold over 3.0 metres in hole 17 Assessment Report 24998
		Drill Core			
1996	N	Assay/analysis	Copper	0.128 %	sample PM-W-4/N-4. No sample descriptions is provided but it likely they are float boulder samples. Assessment Report 24542
		Grab	Silver	29.8 g/t	
1996	N	Assay/analysis Grab	Molybdenum	0.177 %	other samples (K96-PM-1/K-1 and PM-W-7/N-7), located approximately 550 metres to the south east and 1 kilometres to the south west of the previous sample, assayed 0.177 and 0.048 per cent molybdenum, 0.514 and 0.152 per cent copper, 5.6 and 2.0 grams per tonne silver with 0.126 and 0.025 gram per tonne gold, respectively. No sample descriptions are provided but it likely they are float boulder samples. Assessment Report 24542
			Copper	0.514 %	
			Silver	5.6 g/t	
			Gold	0.126 g/t	
1990	N	Assay/analysis Grab	Copper	2.4 %	mineralized float samples Assessment Report 21473
			Molybdenum	1.0 %	
			Silver	24 g/t	
			Gold	0.900 g/t	
1989	N	Assay/analysis Grab	Molybdenum	0.611 %	three mineralized float samples (111310 through 111313) yielded values up to 0.611 per cent molybdenum, 0.204 per cent copper, 33.9 grams per tonne silver and 0.103 gram per tonne gold Assessment Report 19115
			Copper	0.204 %	
			Silver	33.9 g/t	
			Gold	0.103 g/t	