

MINFILE Number:	093K 116	Name:	BAPTISTE (DECAR)	Status:	Developed Prospect
------------------------	----------	--------------	------------------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TOTAL		1,995,873 kt Indicated	Nickel	0.122 %	Using a 0.06 nickel cut-off grade. Grandillo, A., Voordouw, R. (2021-03-17): NI 43-101 Technical Report, Preliminary Economic Assessment, Baptiste Nickel Project, British Columbia, Canada
2020	Y				
TOTAL		592,890 kt Inferred	Nickel	0.114 %	Using a 0.06 nickel cut-off grade. Grandillo, A., Voordouw, R. (2021-03-17): NI 43-101 Technical Report, Preliminary Economic Assessment, Baptiste Nickel Project, British Columbia, Canada
2020	Y				
PIT		1,842,645 kt Indicated	Nickel	0.123 %	A pit-constrained updated mineral resource estimate. Voordouw, R.J., Simpson, R.G. (2018-02-26): 2018 Technical (N.I. 43-101) Report on the Decar Nickel-Iron Alloy Property
2018	Y				
PIT		390,788 kt Inferred	Nickel	0.115 %	A pit-constrained updated mineral resource estimate. Voordouw, R.J., Simpson, R.G. (2018-02-26): 2018 Technical (N.I. 43-101) Report on the Decar Nickel-Iron Alloy Property
2018	Y				
TOTAL		1,160,000 kt Indicated	Nickel	0.124 %	Information Circular 2018-1, page 47.
2013	Y				
TOTAL		870,000 kt Inferred	Nickel	0.125 %	Information Circular 2018-1, page 47.
2013	Y				