

| | | | | | |
|------------------------|----------|--------------|---------|----------------|----------|
| MINFILE Number: | 094E 122 | Name: | WRICH 1 | Status: | Prospect |
|------------------------|----------|--------------|---------|----------------|----------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------------|-----------|-------------|--|
| 1999 | N | Assay/analysis Rock | Zinc | 0.30 % | A sample (DR-4) of potassium feldspar-quartz vein material from the northern mineralized zone. Assessment Report 26251. |
| | | | Gold | 0.99 g/t | |
| | | | Silver | 12.3 g/t | |
| | | | | | |
| 1988 | | Assay/analysis Drill Core | Silver | 94.5000 g/t | Drill core sample over the interval 44.96 to 47.96 metres from drillhole 2 on vein 4. Assessment Report 18098. |
| | | | Copper | 0.4920 % | |
| | | | Lead | 0.7289 % | |
| | | | Zinc | 9.9900 % | |
| 1987 | N | Assay/analysis Grab | Gold | 160.5 g/t | A sample (6929), taken from a 5 to 10-centimetre-wide quartz-carbonate vein (no. 4), while other grab samples from the veins yielded values up to 1.3 per cent copper, 3.1 per cent lead, 9.0 per cent zinc and 364.1 grams per tonne silver. Assessment Report 17459. |
| | | | Silver | 111.6 g/t | |
| | | | Lead | 1.91 % | |
| | | | Zinc | 2.6 % | |
| 1981 | N | Assay/analysis Grab | Silver | 60.9 g/t | A grab sample (CG-LT-15) of quartz vein with pyrite, chalcopyrite, galena, sphalerite and azurite. Assessment Report 10705. |
| | | | Copper | 0.413 % | |
| | | | Lead | 5.89 % | |
| | | | Zinc | 3.16 % | |
| | | | Gold | 0.24 g/t | |