

MINFILE Number:	094E 171	Name:	JD (FINN)	Status:	Prospect
------------------------	----------	--------------	-----------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VENT			Gold	2.28 g/t	Drilling results included 2.28 grams per tonne gold over 5 metres in hole JD-13-020, located near the previous step-out hole JD-12-015 Assessment Report 34762
2013	N	Assay/analysis Drill Core			
DRILLHOLE			Gold	3.0 g/t	Eleven drill holes (JD-12-001 through -011) on the main Finn zone yielded an average of 3.0 grams per tonne gold and 33.6 grams per tonne silver over 23.8 metres, including 8.8 grams per tonne gold and 64.5 grams per tonne silver over 15.6 metres in hole JD-12-003 Assessment Report 33556
2012	N	Assay/analysis Drill Core	Silver	33.6 g/t	
VENT			Gold	1.55 g/t	step-out drill hole (JD-12-015) was collar approximately 400 metres north of the Finn zone on a large gossan and intersected 56 metres of disseminated pyrite +/- sphalerite hosted in strongly silica-sericite altered and locally hydrothermally micro-brecciated andesite yielding five separate zones of mineralization including 1.55 grams per tonne gold over 20 metres and 2.43 grams per tonne gold over 5 metres Assessment Report 33556
2012	N	Assay/analysis Drill Core			
DRILLHOLE			Gold	6.8 g/t	Significant intercepts included 6.8 grams per tonne gold over 17.43 metres in hole JD95-41 to 109.3 grams per tonne gold over 2.0 metres, including 214.9 grams per tonne gold over 1.0 metre in hole JD95-47 Assessment Report 24284
1995	N	Assay/analysis Drill Core			
MAIN		488,370 t Combined	Gold	6.33 g/t	Drilling indicated a probable and possible resource of 488,370 tonne grading 6.33 grams per tonne gold was reported for the Finn zone Assessment Report 24284
1995	N				
MAIN		147,889 t Possible	Gold	4.40 g/t	George Cross News Letter, No.9 (January 13), 1995; Assessment Report 23663
1994	Y				
DRILLHOLE			Gold	4.40 g/t	The drilling partially defined a moderately north dipping, 45- metre thick zone over a strike length of 115 metres yielding a weighted average grade of 4.40 grams per tonne gold (Assessment Report 23663). Markedly higher grades were present in both the hangingwall and footwall of the zone with an average of 6.64 grams per tonne gold over an average width of 3.81 metres for the upper or hangingwall zone and 8.45 grams per tonne gold over an average width of 3.11 metres for the lower or footwall zone Assessment Report 23663
1994	N	Assay/analysis Drill Core			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VENT		Assay/analysis	Gold	7.77 g/t	grab sample 94-M-JD-R-007 from the Vent zone
			Silver	245.0 g/t	Assessment Report 23663
1994	N	Grab			
TRENCHES		Assay/analysis	Gold	7.5 g/t	trenching on the Finn zone yielded 4.5 grams per tonne
1988	N				gold over 40 metres, including 8.0 grams per tonne gold over 17.0 metres in trench JD88-67; 2.2 grams per tonne gold over 21.0 metres, including 18.3 grams per tonne gold over 1.0 metre in trench JD88-68, 19.4 grams per tonne gold over 6.0 metres in trench JD88-70, 6.4 grams per tonne gold over 15.3 metres in trench JD88-76 and 7.5 grams per tonne gold over 43.5 metres, including 41.9 grams per tonne gold over 5.5 metres in trench JD88-78
					Assessment Report 18015