



*MINFILE Inventory Detail Report*  
*BC Geological Survey*  
*Ministry of Energy, Mines and Petroleum Resources*

<b>MINFILE Number:</b>	094K 050	<b>Name:</b>	TORO	<b>Status:</b>	Developed Prospect
------------------------	----------	--------------	------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
RIDGE			Copper	4.37 %	Rock samples (Y646056 and Y646003) from the north and south ridges of the Toro occurrence area yielded values up to 4.37 and 2.57 per cent copper, respectively. Assessment Report 38880.
2020	N	Assay/analysis Rock			
SAMPLE			Copper	7.44 %	Chip samples (B374289 and B374339), from the Toro occurrence area yielded 7.44 and 8.23 per cent copper over 2.00 and 1.50 metres, respectively, while a select sample (B374338) assayed 29.8 per cent copper and 3.1 grams per tonne silver. Harrington, E. (2015-10-23): Technical Report on the Toro Property.
2005	N	Assay/analysis Chip			
TOTAL		1,423,860 t	Copper	3.4200 %	Proven and probable reserves calculated as part of a 1970 feasibility study by MacDonald Consultants. T. Schroeter, personal communication, 1997.
1970	Y	Combined			