

MINFILE N	umber:	104B 338	Name: KINO	G	Status: Showing
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH		Assay/analysis	Silver Lead	294.7 g/t 6.04 %	Sample over a 6 metre thickness within the best mineralized section of Trench H.
2015	Y	Chip	Zinc	13.35 %	Assessment Report 35920
TRENCH		Assay/analysis Chip		1 0.85 %	Trench A sample over a 5 metre width. Assessment Report 35920
2015	Y		Zinc		
KING VEIN		A scov/omolycoic	Silver Gold	122.0000 g/t 864.0000 g/t	20.0 centimetre chip sample taken across the King Vein and adjacent wallrock.
1988	N	Assay/analysis Chip		C	Statement of Material Facts #66/88, Adrian Resources Ltd., Aug.5/88.
SAMPLE		Assay/analysis	Gold	34.29 g/t	Chip samples indicate a weighted average grade of 34.29 gold over an average vein width of 0.30 metres.
1988	Ν	Chip			Assessment Report 18129.