

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN  2003	N	Assay/analysis Drill Core	Gold	2.35 g/t	over 4.0 metres
			Silver	19.25 g/t	Assessment Report 27328
			Copper	0.23 %	
			Lead	0.65 %	
			Zinc	3.16 %	
NORTH  1993	N	Assay/analysis Drill Core	Gold	8.55 g/t	over 3.05 metres
			Silver		Property File - Sway Resources Inc., Statement of
			Zinc		Material Facts, dated February 14, 1994
PIT  1990	N	Assay/analysis Grab	Gold	6.4 g/t	a sample (BCS 18492) from a mineralized quartz vein
			Silver	40.3 g/t	exposed in a pit assayed 6.4 grams per tonne gold, 40.3
			Zinc	1 %	grams per tonne silver and greater than 1.0 per cent zinc
			Lead	1 %	and lead, respectively
		Property File - L. Lee [1990-06-01]: Property report: Franklin Camp			
SAMPLE  1987	N	Assay/analysis Grab	Gold	1.13 g/t	Grab sample number 16783, collected 50 metres
			Silver	48.0 g/t	southeast of the Banner adit
			Copper	0.97 %	Assessment Report 17273
			Zinc	3.08 %	
			Lead	4.48 %	
PIT  1987	N	Assay/analysis Grab	Silver	45.0000 g/t	Sample number 16794 was collected from a pit 240
			Gold	9.2700 g/t	metres north- northeast of the adit.
			Copper	0.2700 %	Assessment Report 17273.
			Lead	2.1200 %	
			Zinc	6.0000 %	
DUMP  1984	N	Assay/analysis Grab	Gold	6.5 g/t	dump samples
			Silver	375.5 g/t	Property File - Starlight Energy Corporation
			Copper	0.91 %	[1984-03-30]: News - Properties Acquired in
			Lead	37.80 %	Greenwood Area - Starlight Energy Corp.
			Zinc	16.40 %	
TRENCH  1970	N	Assay/analysis Chip	Gold	1.4 g/t	An old trench, 7.5 metres north of the shaft, assayed
			Silver	122.8 g/t	1.4 grams per tonne gold, 122.8 grams per tonne silver,
			Copper	1.14 %	1.14 per cent copper, 6.65 per cent lead and 3.45 per
			Lead	6.65 %	cent zinc over 9.0 metres
			Zinc	3.45 %	Property File - R.W. Phandler [1970-06-19]: Report on the Franklin Camp Grand Forks, British Columbia for Great Plains Development Co. of Canada Ltd.

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TUNNEL 1969	Assay/analysis N	Copper Zinc Silver	0.37 % 2.91 % 20.5 g/t	A silicified zone was identified from 43.5 to 52.5 metres down the tunnel with the central 6 metres averaging 0.37 per cent copper, 2.91 per cent zinc and 20.5 grams per tonne silver, a sample from the south rib of the tunnel yielded 0.76 per cent copper, 0.25 per cent lead, 3.96 per cent zinc and 14.4 grams per tonne silver Property File - G.W.H. Norman [1969-01-01]: Franklin Project Grand Forks Area - 1969 - Field Work, Geological Considerations and Results - Geochemical Soil & Stream Sediment Survey
SHAFT 1969	Assay/analysis N	Gold Grab	20.2 g/t	a sample from the Banner shaft Property File - G.W.H. Norman [1969-01-01]: Franklin Project Grand Forks Area - 1969 - Field Work, Geological Considerations and Results - Geochemical Soil & Stream Sediment Survey