

MINFILE Number:	082ENE027	Name:	AU	Status:	Past Producer
------------------------	-----------	--------------	----	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE			Silver	794 g/t	
2012	N	Assay/analysis	Gold	45.7 g/t	Press Release, Tower Resources, November 21, 2012
		Grab	Lead	7.82 %	
			Zinc	3.63 %	
SAMPLE			Silver	141 g/t	One of 39 samples, total average of the 39 samples was 112 grams per tonne silver and 0.9 grams per tonne gold. http://www.towerresourcesltd.com
2011	N	Assay/analysis	Gold	25.4 g/t	
		Grab	Lead	1.8 %	
SHAFT			Gold	68.4 g/t	Samples from a shaft Property File - Cous Creek Copper Mines Ltd. [1983-12-09]: News - Cous Creek Copper Mines Ltd. - Waterloo Mine
1983	N	Assay/analysis	Silver	837.9 g/t	
		Rock	Lead	10.5 %	
			Zinc	8 %	
VEIN			Gold	4.1 g/t	samples of a second, north striking, quartz-pyrite vein Property File - Cous Creek Copper Mines Ltd. [1983-12-09]: News - Cous Creek Copper Mines Ltd. - Waterloo Mine
1983	N	Assay/analysis	Silver	17250.5 g/t	
		Rock			
DUMP			Gold	6.5 g/t	Two dump grab samples averaged Property File - J.C. Stephen [1967-10-20]: Report - Lightning Peak Area - Mastodon Highland Bell Mines Ltd.
1967	N	Assay/analysis	Silver	164.2 g/t	
		Grab	Lead	0.88 %	
			Zinc	0.48 %	
SAMPLE			Silver	838.0000 g/t	Grab sample of 25-centimetre wide vein exposed at 3 metres depth in shaft. Geological Survey of Canada Summary Report 1930A, page 104A.
1930	N	Assay/analysis	Gold	4.1000 g/t	
		Grab	Lead	13.0000 %	
			Zinc	4.5000 %	