

<b>MINFILE Number:</b> 082ENE027	<b>Name:</b> AU	<b>Status:</b> Past Producer
----------------------------------	-----------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Silver	794 g/t	
	Assay/analysis	Gold	45.7 g/t	Press Release, Tower Resources, November 21, 2012
2012	Grab	Lead	7.82 %	
		Zinc	3.63 %	
SAMPLE		Silver	141 g/t	One of 39 samples, total average of the 39 samples was
	Assay/analysis	Gold	25.4 g/t	112 grams per tonne silver and 0.9 grams per tonne
2011	Grab	Lead	1.8 %	gold.
				<a href="http://www.towerresourcesltd.com">http://www.towerresourcesltd.com</a>
SHAFT		Gold	68.4 g/t	Samples from a shaft
	Assay/analysis	Silver	837.9 g/t	Property File - Cous Creek Copper Mines Ltd.
1983	Rock	Lead	10.5 %	[1983-12-09]: News - Cous Creek Copper Mines Ltd. -
		Zinc	8 %	Waterloo Mine
VEIN		Gold	4.1 g/t	samples of a second, north striking, quartz-pyrite vein
	Assay/analysis	Silver	17250.5 g/t	Property File - Cous Creek Copper Mines Ltd.
1983	Rock			[1983-12-09]: News - Cous Creek Copper Mines Ltd. -
				Waterloo Mine
DUMP		Gold	6.5 g/t	Two dump grab samples averaged
	Assay/analysis	Silver	164.2 g/t	Property File - J.C. Stephen [1967-10-20]: Report -
1967	Grab	Lead	0.88 %	Lightning Peak Area - Mastodon Highland Bell Mines
		Zinc	0.48 %	Ltd.
SAMPLE		Silver	838.0000 g/t	Grab sample of 25-centimetre wide vein exposed at 3
	Assay/analysis	Gold	4.1000 g/t	metres depth in shaft.
1930	Grab	Lead	13.0000 %	Geological Survey of Canada Summary Report 1930A,
		Zinc	4.5000 %	page 104A.