

|                                  |                        |                              |
|----------------------------------|------------------------|------------------------------|
| <b>MINFILE Number:</b> 082ENW002 | <b>Name:</b> BLUE HAWK | <b>Status:</b> Past Producer |
|----------------------------------|------------------------|------------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category              | Commodity      | Grade                  | Reference/<br>Comments  |
|-----------------------------|-----------------------------------|----------------|------------------------|---|
| SAMPLE<br>2012              | N<br>Assay/analysis<br>Rock       | Gold           | 4.24 g/t               | A sample (no. 1) from a quartz vein proximal to the historic workings.<br>Assessment Report 34142   |
| NORTHWEST<br>2004           | N<br>Assay/analysis<br>Grab       | Copper         | 0.239 %                | A grab sample (4304) from the northwest trending shear, taken approximately 1 kilometre northwest of the adits.<br>Assessment Report 27447  |
| DRILLHOLE<br>1989           | N<br>Assay/analysis<br>Drill Core | Gold           | 0.565 g/t              | Over 1.00 metre in hole K93-02.<br>Assessment Report 23811  |
| TRENCH<br>1988              | N<br>Assay/analysis<br>Chip       | Gold<br>Silver | 19.39 g/t<br>67.98 g/t | The average assay of 10 channel samples from Trench #1.<br>Property File - Dasler P.G., 1989  |
| TRENCH<br>1984              | N<br>Assay/analysis<br>Grab       | Gold<br>Silver | 8.3 g/t<br>22.9 g/t    | A sample (AB-4) from trench no. 5 on the E5 vein.<br>Assessment Report 12732  |
| TRENCH<br>1981              | N<br>Assay/analysis<br>Chip       | Gold<br>Silver | 14.4 g/t<br>111.2 g/t  | F1 trench over 1.3 metres, located northwest of the adits.<br>Assessment Report 9414  |
| TRENCH<br>1981              | N<br>Assay/analysis<br>Chip       | Gold<br>Silver | 13.7 g/t<br>268.5 g/t  | Over 0.4 metre of E5 trench, located southwest of the main adit.<br>Assessment Report 9414  |
| SHAFT<br>1980               | N<br>Assay/analysis<br>Chip       | Gold<br>Silver | 130.6 g/t<br>476.1 g/t | Chip sampling of a surface exposure of a 0.40 metre wide sericitized and sheared quartz vein with pyrite, located near an inferred air shaft for the underground workings, over the most pyritic 0.2 metre of the vein and 15.7 grams per tonne gold with 58.8 grams per tonne silver over the full 0.40-metre-wide vein.<br>Assessment Report 9074 |
| TRENCH<br>1972              | N<br>Assay/analysis<br>Chip       | Gold<br>Silver | 30.1 g/t<br>87.2 g/t   | Silver in trench 6 which is believed to have exposed the northwest extension of the D vein.<br>Property File 000910   |

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category        | Commodity                | Grade                        | Reference/<br>Comments   |
|-----------------------------|-----------------------------|--------------------------|------------------------------|--|
| TRENCH<br>1972              | N<br>Assay/analysis<br>Chip | Gold<br>Silver<br>Copper | 1.7 g/t<br>8.6 g/t<br>0.30 % | In trench 12 which exposed an altered diorite and pyritic sediments, located south of the adits.<br>Property File 000910 |
| DRIFT<br>1967               | N<br>Assay/analysis<br>Chip | Gold<br>Silver           | 34.2 g/t<br>136.8 g/t        | Sampling the D vein exposed in a short drift of the shaft over 0.72 metre.<br>Assessment Report 12519                    |
| DRIFT<br>1966               | N<br>Assay/analysis<br>Chip | Gold<br>Silver           | 92.3 g/t<br>307.8 g/t        | Sampling the D vein exposed in a short drift of the shaft over 0.21 metre.<br>Assessment Report 12519                    |