

<b>MINFILE Number:</b> 082ESE044	<b>Name:</b> RUBY (L.1333)	<b>Status:</b> Past Producer
----------------------------------	----------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE  1969	N  Assay/analysis Chip	Copper Silver	19.39 % 297.5 g/t	<p>sampling yielded up to 1.47 per cent copper over 12 metres at site 1, 3.37 per cent copper over 6 metres at site 2 with grab samples yielding up to 27.88 per cent copper, 19.39 per cent copper with 297.5 grams per tonne silver over 1.5 metres from site 3, 1.15 per cent copper over 1.5 metres at site 4, 1.40 per cent copper over 2.4 metres at site 5 and 10.50 per cent copper over 0.45 metre at site 6</p> <p>Property File - Pierre G. Lacombe [1969-04-28]: Report on the Ruby Claims</p>
SHAFT  1961	N  Assay/analysis Chip	Silver Copper	6.8 g/t 0.35 %	<p>a chip sample from the wall of the southern shaft</p> <p>Property File - D. Irving [1961-05-01]: Chain and Compass Survey - Ruby Mine</p>
TRENCH  1961	N  Assay/analysis Chip	Gold Silver Copper	0.5 g/t 15.4 g/t 3.59 %	<p>a random chip sample of oxidized material from a trench yielded 0.5 gram per tonne gold, 15.4 grams per tonne silver and 2.57 per cent copper with 1.02 per cent copper oxide</p> <p>Property File - D. Irving [1961-05-01]: Chain and Compass Survey - Ruby Mine</p>