

MINFILE Number:	082ESE044	Name:	RUBY (L.1333)	Status:	Past Producer
------------------------	-----------	--------------	---------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE			Copper	19.39 %	sampling yielded up to 1.47 per cent copper over 12 metres at site 1, 3.37 per cent copper over 6 metres at site 2 with grab samples yielding up to 27.88 per cent copper, 19.39 per cent copper with 297.5 grams per tonne silver over 1.5 metres from site 3, 1.15 per cent copper over 1.5 metres at site 4, 1.40 per cent copper over 2.4 metres at site 5 and 10.50 per cent copper over 0.45 metre at site 6
			Silver	297.5 g/t	
1969	N	Assay/analysis Chip			Property File - Pierre G. Lacombe [1969-04-28]: Report on the Ruby Claims
SHAFT			Silver	6.8 g/t	a chip sample from the wall of the southern shaft
			Copper	0.35 %	
1961	N	Assay/analysis Chip			Property File - D. Irving [1961-05-01]: Chain and Compass Survey - Ruby Mine
TRENCH			Gold	0.5 g/t	a random chip sample of oxidized material from a trench yielded 0.5 gram per tonne gold, 15.4 grams per tonne silver and 2.57 per cent copper with 1.02 per cent copper oxide
			Silver	15.4 g/t	
			Copper	3.59 %	
1961	N	Assay/analysis Chip			Property File - D. Irving [1961-05-01]: Chain and Compass Survey - Ruby Mine