

<b>MINFILE Number:</b>	082ESE123	<b>Name:</b>	CROESUS (L.866)	<b>Status:</b>	Showing
------------------------	-----------	--------------	-----------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1997	N	Assay/analysis	Gold	1.5 g/t	over 1.5 metres
		Drill Core			Assessment Report 25422
1990	N	Assay/analysis	Silver	3.0 g/t	samples of massive pyrrhotite-pyrite-chalcopyrite from the Croesus trench
		Grab	Copper	0.387 %	
1990	N	Assay/analysis	Silver	7.8 g/t	samples of massive pyrrhotite-pyrite-chalcopyrite from the Croesus adit
		Chip	Copper	0.714 %	
1990	N	Assay/analysis	Silver	2.4 g/t	a sample of south eastern quartz vein
		Grab	Copper	0.05 %	
			Lead	0.09 %	Property File - Bombini, S. [1990-07-01]: Property report: Croesus-Johannesburg
1983	N	Assay/analysis	Copper	0.38 %	chip sample (ASH 83-9) of massive sulphides from the upper workings yielded 0.38 per cent copper over 2.8 metres
		Chip			
1983	N	Assay/analysis	Copper	0.45 %	a chip sample (ASH 83-6) of massive sulphides from the lower Croesus workings yielded 0.45 per cent copper and 6.8 grams per tonne silver over 1.0 metre
		Chip	Silver	6.8 g/t	
1968	N	Assay/analysis	Silver	6.9000 g/t	Assessment Report 1648.
		Chip	Copper	1.6100 %	