

| | | |
|----------------------------------|---------------------------------|------------------------------|
| MINFILE Number: 082ESE153 | Name: GOLD DROP (L.1415) | Status: Past Producer |
|----------------------------------|---------------------------------|------------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments | |
|-----------------------------|----------------------|-----------|--------------|---|---|
| SAMPLE | | Silver | 26 g/t | Assay from sample number GD-R-15-13. | |
| | Assay/analysis | Gold | 19.95 g/t | Martin, D. (2016-07-12): National Instrument 43-101 | |
| 2014 | Y | Grab | Copper | 0.21 % | Technical Report on the Gold Drop Property. |
| | | | Lead | 0.34 % | |
| VEIN | | Gold | 100.00 g/t | The grades were the maximum from four samples taken from the main vein. | |
| | Assay/analysis | Silver | 229.3 g/t | Martin, D. (2016-07-12): National Instrument 43-101 | |
| 1990 | Y | Rock | Lead | 1.48 % | Technical Report on the Gold Drop Property. |
| | | | Copper | 0.58 % | |
| VEIN | | Silver | 164.5000 g/t | George Cross Newsletter #189, October 1, 1984. | |
| | Assay/analysis | Gold | 39.4000 g/t | | |
| 1984 | N | Grab | | | |