MINFILE Number: 082ESW158 **Name:** FLORENCE **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN 2009 N	Assay/analysis Chip	Gold Silver Copper Lead Zinc	11.910 g/t 12.7 g/t 0.189 % 0.186 % 0.738 %	two chip samples (F-BDRL17 and F-BDRL19) of quartz-carbonate veins assayed 11.910 and 5.060 grams per tonne gold, 13.7 and 20.2 grams per tonne silver, 0.189 and 0.180 per cent copper, 0.186 and 1.050 per cent lead with 0.738 and 1.010 per cent zinc over 20 and 39 centimetres, respectively Gray, P.D. (2010-05-28): Technical Report on the Beaverdell Property
VEIN 1980	Assay/analysis Channel	Silver Gold Copper Lead Zinc	15.7700 g/t 13.6400 g/t 0.0800 % 0.0500 % 0.3600 %	Sample 15658, a 20.32-centimetre channel sample across 7.62 centimetres of altered granodiorite and 12.70 centimetres of quartz veinlets. Assessment Report 8196.