MINFILE Number: 082FNE065 **Name:** COPPER KING (L.3835) **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SILVERTIP 2010 N	Assay/analysis Rock	Copper Bismuth Silver Gold	9.99 % 0.20 % 167 g/t 1.09 g/t	samples (SK10-259, -260 and -263 to -265) from a quartz breccia zone, located on the Silvertip (L.3840) claim, yielded values from 0.05 to 9.99 per cent copper, 0.05 to greater than 0.20 per cent bismuth, 5.2 to 167 grams per tonne silver and 0.10 to 1.09 grams per tonne gold Assessment Report 32263
VEIN 2010 N	Assay/analysis Rock	Copper Silver Gold Bismuth	3.74 % 79.7 g/t 13.36 g/t 0.20 %	A rock sample (SK10-235) from a narrow quartz-carbonate-iron oxide vein with chalcopyrite assayed 3.74 per cent copper, greater than 0.20 per cent bismuth, 79.7 grams per tonne silver and 13.36 grams per tonne gold Assessment Report 32263
WORKINGS 2010 N	Assay/analysis Rock	Copper Zinc Antimony Silver Gold	2.62 % 0.22 % 0.20 % 271 g/t 1.26 g/t	a sample (SK10-238) from the best 0.5 metre section of a mineralized quartz-carbonate vein exposed in historic workings yielded 2.62 per cent copper, 0.22 per cent zinc, greater than 0.20 per cent antimony, 271 grams per tonne silver and 1.26 grams per tonne gold Assessment Report 32263
COPPER 1980 N	Assay/analysis Rock	Lead Zinc Copper Silver Gold	0.20 % 0.87 % 9.77 % 99.8 g/t 2.39 g/t	Rock samples from the Copper King occurrence area yielded values from trace to 0.20 per cent lead, trace to 0.87 per cent zinc, trace to 9.77 per cent copper, trace to 99.8 grams per tonne silver and trace to 2.39 grams per tonne gold Assessment Report 9105