

MINFILE Number: 082FNE065	Name: COPPER KING (L.3835)	Status: Showing
----------------------------------	-----------------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SILVERTIP		Copper	9.99 %	samples (SK10-259, -260 and -263 to -265) from a quartz breccia zone, located on the Silvertip (L.3840) claim, yielded values from 0.05 to 9.99 per cent copper, 0.05 to greater than 0.20 per cent bismuth, 5.2 to 167 grams per tonne silver and 0.10 to 1.09 grams per tonne gold Assessment Report 32263
2010	N	Bismuth	0.20 %	
	Assay/analysis	Silver	167 g/t	
	Rock	Gold	1.09 g/t	
VEIN		Copper	3.74 %	A rock sample (SK10-235) from a narrow quartz-carbonate-iron oxide vein with chalcopyrite assayed 3.74 per cent copper, greater than 0.20 per cent bismuth, 79.7 grams per tonne silver and 13.36 grams per tonne gold Assessment Report 32263
2010	N	Silver	79.7 g/t	
	Assay/analysis	Gold	13.36 g/t	
	Rock	Bismuth	0.20 %	
WORKINGS		Copper	2.62 %	a sample (SK10-238) from the best 0.5 metre section of a mineralized quartz-carbonate vein exposed in historic workings yielded 2.62 per cent copper, 0.22 per cent zinc, greater than 0.20 per cent antimony, 271 grams per tonne silver and 1.26 grams per tonne gold Assessment Report 32263
2010	N	Zinc	0.22 %	
	Assay/analysis	Antimony	0.20 %	
	Rock	Silver	271 g/t	
		Gold	1.26 g/t	
COPPER		Lead	0.20 %	Rock samples from the Copper King occurrence area yielded values from trace to 0.20 per cent lead, trace to 0.87 per cent zinc, trace to 9.77 per cent copper, trace to 99.8 grams per tonne silver and trace to 2.39 grams per tonne gold Assessment Report 9105
1980	N	Zinc	0.87 %	
	Assay/analysis	Copper	9.77 %	
	Rock	Silver	99.8 g/t	
		Gold	2.39 g/t	