

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
VEIN 1998	N	Assay/analysis Drill Core	Zinc Silver Cadmium	47.37 % 7.1 g/t 0.268 %	diamond drilling (DDH S98-1) intercepted a 3 centimetre wide vein of sphalerite with traces of galena cut by fine calcite veins with minor pyrrhotite and trace chalcopyrite, at depth of 84.2 metres and hosted by calc-silicate rocks Assessment Report 25750
SAMPLE 1981	N	Assay/analysis Drill Core	Dolomite	20.0 %	Drill core samples yielded from 25.9 to 29.6 per cent calcium oxide and 15.1 to 20.0 per cent magnesium oxide Assessment Report 10247
SAMPLE 1973	N	Assay/analysis Drill Core	Dolomite	16.80 %	A sample of cored dolomite contained 27.70 per cent calcium oxide, 16.80 per cent magnesium oxide, 14.12 per cent silicon dioxide, trace of aluminium oxide, 0.52 per cent iron oxide and 39.94 per cent ignition loss Assessment Report 4923
SAMPLE 1944	N	Assay/analysis Grab	Dolomite	20.1800 %	From southwest end of band. Grade given for MgO. CANMET Report 811, page 212-Sample 85A.