

MINFILE Number: 082FNE091	Name: WELCOME & ENTERPRISE	Status: Prospect
----------------------------------	-----------------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Silver	12.8 g/t	A rock sample (C0146665) from a phyllite hosting carbonate lenses/beds, up to 0.15 metre thick, with pyrite-pyrrhotite-sphalerite and minor chalcopyrite, located at an elevation of approximately 2380 metres on the north face of Hungry Peak, assayed greater than 1.00 per cent zinc with 12.8 grams per tonne silver Assessment Report 41925
2022	N Assay/analysis Rock			
CREEK		Copper	0.62 %	Two dump samples (BCU22-05 and -06) from the Creek zone yielded 2.94 and 0.62 per cent copper, 0.88 and 11.74 per cent lead, 84.7 and 287.0 grams per tonne silver with 0.17 and 0.10 gram per tonne gold, respectively Assessment Report 40962
		Lead	11.74 %	
2021	N Assay/analysis Grab	Silver	287.0 g/t	
		Gold	0.10 g/t	
LOWER		Copper	1.11 %	two outcrop samples (BCU22-01 and -02) from the lower workings (4300-level) on the Welcome claim yielded 0.69 and 1.11 per cent copper with 13.1 and 15.2 grams per tonne silver, respectively Assessment Report 40962
		Silver	15.2 g/t	
2021	N Assay/analysis Rock			
ADIT		Copper	1.31 %	A chip sample (BC12A-09) across a malachite-stained shear zone in limy quartzite-sericite schist at an elevation of approximately 1350 metres yielded 1.03 per cent copper and 15.2 grams per tonne silver over 2.75 metres, while a select grab sample (BC12A-08) taken from a nearby adit portal assayed 1.31 per cent copper and 22.8 grams per tonne silver Assessment Report 33347
		Silver	22.8 g/t	
2012	N Assay/analysis Rock			
LOWER		Copper	2.23 %	Two rock samples (3595 and 3596) taken from or near an area of historic workings at an elevation of approximately 1250 metres and near the southwest corner of the Surprise L.1626 claim yielded 2.23 and 3.29 per cent copper, 2.19 and 0.06 per cent lead with 99.5 and 75.6 grams per tonne silver, respectively Assessment Report 18258
		Lead	2.19 %	
1987	N Assay/analysis Rock	Silver	99.5 g/t	
CREEK		Lead	52.10 %	sample (3597) taken from the Creek zone Assessment Report 18258
		Silver	478.8 g/t	
1987	N Assay/analysis Rock			
FOOTWALL		Lead	15.90 %	sampling of the 4600-level (Creek) zone is reported to have yielded values of up to 15.90 per cent lead, 0.26 per cent copper and 164.7 grams per tonne silver over 2.3 metres from the footwall of the shear Assessment Report 6206
		Silver	164.7 g/t	
1976	N Assay/analysis Chip	Copper	0.26 %	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
HANGINGWALL 1976	N	Assay/analysis Chip	Copper	4.41 %	sampling of the 4600-level (Creek) zone is reported to have yielded an average of 4.41 per cent copper with 22.7 grams per tonne silver over 4.4 metres from the hangingwall of the shear Assessment Report 6206
			Silver	22.7 g/t	
ADIT 1976	N	Assay/analysis Chip	Copper	2.90 %	Sampling of the north cross-cut yielded 1.20 per cent copper over 3.0 metres, while the south cross-cut yielded 2.90 per cent copper over 3.4 metres Assessment Report 6206
UPPER 1961	N	Assay/analysis Rock	Copper	1.77 %	Sampling of trenches above the 5000-level are reported to have yielded values up to 1.77 per cent copper over 3.0 metres Assessment Report 6206