

MINFILE Number: 082FNE100	Name: BRACEBRIDGE	Status: Prospect
----------------------------------	--------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 2023	N Assay/analysis Rock	Copper Silver	4.89 % 92.7 g/t	Three samples (4061328, P304660 and 4060465) from the historic trench 7 yielded from 1.53 to 4.89 per cent copper with 12.1 to 92.7 grams per tonne silver, while a sample (4060468) from the historic trench 4 assayed 1.02 per cent copper and 57.1 grams per tonne silver Assessment Report 42035
LOWER 2021	N Assay/analysis Chip	Copper Silver	1.81 % 31.0 g/t	a chip sample (P304020) of quartz-siderite chalcopyrite veins hosted in a sericite-altered phyllite from the lower historic drill site yielded 1.81 per cent copper and 31.0 grams per tonne silver over 1.30 metres, while a nearby grab sample (P304019) assayed 2.93 per cent copper and 128 grams per tonne silver Assessment Report 40118
MAIN 2021	N Assay/analysis Rock	Copper Silver	0.88 % 34 g/t	A chip sample (P3040118) from the main workings area assayed 0.88 per cent copper and 34 grams per tonne silver over 1.1 metres, while three nearby grab samples (P304017, P310220 and P304022) of quartz-siderite-pyrite-chalcopyrite veins hosted in the deformation zone yielded values from 2.66 to 12.56 per cent copper with 72 to 147 grams per tonne silver Assessment Report 40118
LOWER 2012	N Assay/analysis Rock	Gold Silver Copper	0.43 g/t 117 g/t 3.85 %	Three samples (BC12-01 to -03) of mineralized float and vein outcrop from the area of the lower (1967) drill site yielded values from 0.14 to 0.43 gram per tonne gold, 62.3 to 117 grams per tonne silver and 2.33 to 3.85 per cent copper Assessment Report 33347
MAIN 2012	N Assay/analysis Rock	Copper Silver	3.18 % 49.6 g/t	four chip and grab samples (BC12A-03 to -06) from elevations of 1749 to 1840 metres near the main zone yielded values from 1.36 to 3.18 per cent copper with 20.0 to 49.6 grams per tonne silver over width of up to 1.0 metre Assessment Report 33347
MIDDLE D 2012	N Assay/analysis Chip	Copper Silver	1.02 % 20.2 g/t	a chip sample (BC12A-02), located at approximately 1600 metres elevation, over 1.8 metres Assessment Report 33347
FLOAT 2007	N Assay/analysis Grab	Gold	35.41 g/t	a float sample (BB-11) of quartz vein hosting pyrite-chalcopyrite, taken below the historic workings Assessment Report 30297

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2007	N Assay/analysis Rock	Gold Silver Copper	0.26 g/t 100 g/t 1 %	Rock samples (BB-22 through BB-27) from a zone of tightly folded phyllites with quartz veining hosting massive chalcopyrite-pyrite mineralization with malachite, azurite and carbonate alteration exposed in the main workings yielded values from 0.03 to 0.26 gram per tonne gold, 27.8 to greater than 100 grams per tonne silver and all greater than 1.00 per cent copper Assessment Report 30297
TRENCHES 1976	N Assay/analysis Rock	Silver Copper	23.3 g/t 0.83 %	Sampling of trenches yielded values of 0.83 per cent copper with 23.3 grams per tonne silver over 5.5 metres from a 1.2 metre wide quartz vein that has been repeatedly folded in trench 1, 2.29 per cent copper with 17.2 grams per tonne silver over 4.5 metres in trench 6 and 0.93 to 4.40 per cent copper with 2.7 to 35.7 grams per tonne silver over widths of 7.0 to 1.1 metres, respectively, in trench 7. Trenches 6 and 7 are reported to have been located near the historic (1966) drill hole 1A. Assessment Report 6206
TRENCHES 1967	N Assay/analysis Rock	Copper Silver	2.28 % 73.4 g/t	Sampling of trenches 2A, 3A and 5A is reported to have yielded values of 2.09, 1.61 and 2.28 per cent copper with 25.7, 69.3 and 73.4 grams per tonne silver over 21.3, 9.1 and 12.2 metres, respectively Assessment Report 6206
LOWER 1967	N Assay/analysis Drill Core	Copper Silver	0.85 % 12.0 g/t	percussion drilling in 1967, located at an elevation of approximately 1300 metres and approximately 950 metres south of the 1966 Cominco drill holes, yielded intercepts including 0.92 and 0.85 per cent copper with 6.2 and 12.0 grams per tonne silver over 12.2 and 9.1 metres in holes S-2 and S-4, respectively Assessment Report 6206
MAIN 1966	N Assay/analysis Drill Core	Copper	1.40 %	In 1966, all holes are reported to have intersected copper values varying from 0.20 to 3.30 per cent copper over widths of 1.5 to 6.9 metres with the best intersection yielding 1.40 per cent copper over 29.7 metres, including 3.30 per cent copper over 4.4 metres in hole DDH 1A. Assessment Report 6206
TRENCH 1966	N Assay/analysis Rock	Copper	0.40 %	sampling of trench 3A is reported to have yielded 0.40 per cent copper over 10.7 metres Assessment Report 6206