

| | | |
|----------------------------------|--------------------------------|------------------------------|
| MINFILE Number: 082FNW145 | Name: WESTMONT (L.8929) | Status: Past Producer |
|----------------------------------|--------------------------------|------------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|----------------------|-----------|---------------|---|
| VEIN | | Silver | 2300.0000 g/t | Sample JL-125. |
| | Assay/analysis | Gold | 0.9740 g/t | Open File 1988-11. |
| 1987 | Grab | Copper | 0.2470 % | |
| | | Lead | 7.8000 % | |
| | | Zinc | 12.9700 % | |
| UNDERGROUND | | Silver | 2363 g/t | diamond drilling, from the north drive, intersected a parallel vein structure, located approximately 60 metres to the west. Two samples of vein material assayed 2363 and 1351 grams per tonne silver |
| | Assay/analysis | | | Property File - Hoko Explorations [1981-04-04]: News Clippings - Westmont |
| 1979 | Drill Core | | | |
| UNDERGROUND | | Silver | 858.4 g/t | sampling of the lowest level averaged 858.4 grams per tonne silver, 7.60 per cent lead and 12.20 per cent zinc |
| | Assay/analysis | Lead | 7.60 % | Property File - Hoko Explorations [1981-04-04]: News Clippings - Westmont |
| 1979 | Chip | Zinc | 12.20 % | |
| UNDERGROUND | | Silver | 778.4 g/t | underground sampling of the fifth level yielded up to 778.4 grams per tonne silver across 30 centimetres, while chip samples from the fourth level yielded up to 1334.1 grams per tonne silver |
| | Assay/analysis | | | Property File - Eastmont Silver Mines [1971-02-01]: Prospectus Report on the Eastmont Property |
| 1968 | Chip | | | |