

<b>MINFILE Number:</b>	082FNW212	<b>Name:</b>	L.H. (L.5738)	<b>Status:</b>	Past Producer
------------------------	-----------	--------------	---------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
UPPER			Gold	175.00 g/t	Diamond drilling yielded intercepts including 1.29 and 0.71 grams per tonne gold over 21.00 and 19.00 metres, respectively, in hole LH15-30; 13.58 grams per tonne gold over 16.90 metres, including 175.00 grams per tonne gold over 1.00 metre in hole LH15-31; 3.81 grams per tonne gold over 57.37 metres in hole LH15-32; 10.20 grams per tonne gold over 5.47 metres in hole LH15-36; 7.08 grams per tonne gold over 9.34 metres in hole L15-37; 20.66 grams per tonne gold over 11.00 metres, including 132.00 grams per tonne gold over 1.00 metre in hole L15-38 and 5.92 grams per tonne gold over 36.00 metres in hole LH15-40 Walker, R.T. (2016-03-09): NI 43-101 Technical Report - LH Property
2015	N	Assay/analysis Drill Core			
DRILLHOLE			Gold	11.40 g/t	diamond drill holes were collard at two separate location on the west side of Fingland Creek to test previously identified magnetic anomalies. Diamond drill yielded intercepts including 0.30 gram per tonne gold over 90.53 metres, including 11.40 grams per tonne gold over 1.00 metre in hole LH-14-26 and 0.28 gram per tonne gold over 113.00 metres, including 3.94 grams per tonne gold over 1.00 metre in hole LH-14-27 Walker, R.T. (2016-03-09): NI 43-101 Technical Report - LH Property
2014	N	Assay/analysis Drill Core			
RIDGE			Gold	14.70 g/t	over 1.00 metre and 0.44 gram per tonne gold over 39.00 metres in hole LH-12-25 Walker, R.T. (2016-03-09): NI 43-101 Technical Report - LH Property
2012	N	Assay/analysis Drill Core			
L.H.		299,375 t	Gold	17.1400 g/t	GCNL June 29, 1988.
1988	Y	Indicated			
TUNNEL			Gold	20.74 g/t	from a 1.0 metre shear (Sample B) on the Ice Tunnel zone Walker, R.T. (2016-03-09): NI 43-101 Technical Report - LH Property
1981	N	Assay/analysis Chip			
VEIN			Gold	11.14 g/t	samples (A) from two 1.0 to 1.5-metre wide quartz veins with pyrrhotite and arsenopyrite assayed 11.14 and 7.27 grams per tonne gold at two locations 50 metres apart Walker, R.T. (2016-03-09): NI 43-101 Technical Report - LH Property
1981	N	Assay/analysis Rock			

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
L.H.  1945            Y	54,430            t Unclassified	Gold	8.5700 g/t	Internal reference is Consolidated Quebec Gold Mining and Metals Corporation Annual Report; January 31, 1946. National Mineral Inventory 082F14 Au3.