

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
MAIN 1981	37,700 t Indicated Y	Silver Gold	104.2000 g/t 8.7500 g/t	Assessment Report 10811.	
OUTCROP 1964	Assay/analysis Chip	Gold Silver	3.4 g/t 51.3 g/t	chip sample (A-6) over 1.6 metres of massive quartz vein material, taken south east of the Valparaiso portal Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties	
DUMP 1964	Assay/analysis Grab	Gold Silver	19.2 g/t 1262.0 g/t	grab samples from the Valparaiso and Government dumps yielded 1.4 and 19.2 grams per tonne gold with 950.8 and 1262.0 grams per tonne silver, respectively Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties	
DRIFT 1964	Assay/analysis Chip	Gold	1.4 g/t	chip samples (A-9 and A-10) across 1.05 metres of quartz vein from the south end of the Government drift, while a 75 centimetre section of granite yielded 0.3 gram per tonne gold with tungsten values Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties	
DRIFT 1956	Assay/analysis Channel	Gold Silver	10.3 g/t 46.5 g/t	average of twenty channel samples of the north end of the vein on the Government drift over a length of 30 metres and a width of 1.95 metres Property File - D.R. Morgan [1984-07-10]: Mining Property Information - Valparaiso, Government	
DRIFT 1956	Assay/analysis Channel	Gold Silver	10.0 g/t 130.3 g/t	average of seven samples from the south end of the vein on the Government drift over a length of 33 metres and a width of 1.25 metres Property File - D.R. Morgan [1984-07-10]: Mining Property Information - Valparaiso, Government	
DRIFT 1956	Assay/analysis Channel	Gold Silver	10.3 g/t 68.4 g/t	from the middle of the Government drift over a length of 54 metres and width of 1.5 metres Property File - D.R. Morgan [1984-07-10]: Mining Property Information - Valparaiso, Government	
SHAFT 1933	Assay/analysis Chip	Gold Silver	18.7 g/t 175.1 g/t	sampling of the middle portion of the Government shaft yielded 18.7 and 14.0 grams per tonne gold with 175.1 and 140.2 grams per tonne silver over a width of 72.5 and 45 centimetres, respectively Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties	

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRIFT 1927	N Assay/analysis Channel	Gold Silver	3.4 g/t 37.6 g/t	average of eleven channel samples from the north end of the Valparaiso drift over a length of 37.5 metres and a width of 1.74 metres Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties
DRIFT 1926	N Assay/analysis Grab	Gold Silver	19.8 g/t 554.0 g/t	grab samples from the south end of the Government drift Property File - Northern Pacific Mines Ltd. [1964-05-20]: Report - Destiny Bay Properties