



MINFILE Inventory Detail Report
BC Geological Survey
Ministry of Energy, Mines and Petroleum Resources

MINFILE Number:		Name:		Status:		
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SAMPLE		Assay/analysis Grab	Silver	249 g/t	Sample AP080-05.	
2008			Gold	1.1 g/t	EMPR ASS RPT 30317	
N			Lead	11.96 %		
			Zinc	0.55 %		
SAMPLE		Assay/analysis Chip	Zinc	12.5 %	Sample 645-RK002 taken over 2.5 metres. EMPR ASS RPT 26135	
1999						
N						
SILVER		49,120	t	Silver	235.0000 g/t	
1981		Measured Drill Core			Proven reserves of silver zone, average thickness of 3.4 metres; with minor lead and zinc (Quadros, 1981). Also 12,180 tonnes of indicated of similar grade material. Taylor, 1984.	
Y			Silver	246.8500 g/t	Weighted average of diamond-drill hole U80-02.	
DRILLHOLE			Gold	2.4000 g/t	Assessment Report 9053.	
1980			Lead	0.3900 %		
N			Zinc	3.9500 %		
ZINC		36,287	t	Zinc	3.1600 %	
1959		Indicated			Cominco's work. Taylor, 1984.	
Y						