

MINFILE Number: 082FSW001	Name: ASPEN (L.12471)	Status: Past Producer
----------------------------------	------------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2008	N Assay/analysis Grab	Silver Gold Lead Zinc	249 g/t 1.1 g/t 11.96 % 0.55 %	Sample AP080-05. EMPR ASS RPT 30317
SAMPLE 1999	N Assay/analysis Chip	Zinc	12.5 %	Sample 645-RK002 taken over 2.5 metres. EMPR ASS RPT 26135
SILVER 1981	Y 49,120 t Measured	Silver	235.0000 g/t	Proven reserves of silver zone, average thickness of 3.4 metres; with minor lead and zinc (Quadros, 1981). Also 12,180 tonnes of indicated of similar grade material. Taylor, 1984.
DRILLHOLE 1980	N Assay/analysis Drill Core	Silver Gold Lead Zinc	246.8500 g/t 2.4000 g/t 0.3900 % 3.9500 %	Weighted average of diamond-drill hole U80-02. Assessment Report 9053.
ZINC 1959	Y 36,287 t Indicated	Zinc	3.1600 %	Cominco's work. Taylor, 1984.