MINFILE Number: 082FSW061 **Name:** UNITED VERDE **Status:** Developed Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT 1996 N	Assay/analysis Grab	Lead Silver Gold	2.66 % 221.1 g/t 0.63 g/t	grab sample (UV4-1) from a pit near the middle adit Assessment Report 24910
UNDERGROUND 1979 N	Assay/analysis Grab	Copper Lead Zinc Silver Gold Molybdenum Tungsten	0.12 % 0.36 % 2.3 % 684 g/t 1.03 g/t 0.007 % 1.9 %	sampling of mineralized veins exposed by the lower adit Assessment Report 7849
UNDERGROUND 1978 N	Assay/analysis Chip	Lead Zinc Silver Copper	5.78 % 5.54 % 106.7 g/t 0.33 %	two samples of vein material from the “Big” and “First” veins from the lower adit yielded 0.29 and 0.33 per cent copper, 5.78 and 0.28 per cent lead, 2.17 and 5.54 per cent zinc with 106.7 and 22.6 grams per tonne silver over 1.2 metres each Assessment Report 7300
DUMP 1978 N	Assay/analysis Grab	Lead Zinc Silver	5.83 % 6.30 % 159.4 g/t	dump samples Assessment Report 7300
LENS 1921	Assay/analysis Chip	Silver Gold Lead Zinc	442.3000 g/t 2.7400 g/t 21.6000 % 1.3000 %	The sample width is 4.57 metres. Geological Survey of Canada, Memoir 172.
UNDERGROUND 1918 N	Assay/analysis Chip	Zinc Lead Silver Gold	1.0 % 3.5 % 136.8 g/t 0.7 g/t	samples of vein material from the lower level over 0.3 metre British Columbia Minister of Mines Report 1918
UNDERGROUND 1918 N	Assay/analysis Rock	Zinc Lead Silver	1.2 % 6.5 % 82.1 g/t	sample of vein material from the upper level raise British Columbia Minister of Mines Report 1918