

MINFILE Number: 082FSW177	Name: REFERENDUM (L.4387)	Status: Past Producer
----------------------------------	----------------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 2012 N	Assay/analysis Rock	Gold	78.1 g/t	a sample containing quartz with banded tourmaline from a trench at the Referendum property V STOCKWATCH, October 19, 2012
OUTCROP 2005 N	Assay/analysis Grab	Gold Copper	1.80 g/t 4.24 %	grab samples from outcrop Assessment Report 27948
DRILLHOLE 2005 N	Assay/analysis Drill Core	Copper Gold	0.252 % 0.86 g/t	Assessment Report 27948
DUMP 1986 N	Assay/analysis Grab	Gold	12.9 g/t	a grab sample of dump material from the second shaft, to the north east Property File - Snowater Resources Ltd. [1986-10-22]: Report on the Referendum Gold Prospect - 1986
NO. 2 VEIN 1986 N	Assay/analysis Chip	Gold	8.6 g/t	Sampling, later that year, of the no. 2 vein yielded up to 82.1 grams per tonne gold over 33 centimetres, with an average of 8.6 grams per tonne gold across 30 centimetres and over a strike length of 30 metres Property File - Snowater Resources Ltd. [1987-03-10]: Report on the Referendum Gold Prospect - 1987
NO. 3 VEIN 1986 N	Assay/analysis Chip	Gold	36.9 g/t	samples from the no. 3 vein yielded up to 36.9 grams per tonne gold over 20 centimetres Property File - Snowater Resources Ltd. [1987-03-10]: Report on the Referendum Gold Prospect - 1987
TRENCHES 1986 N	Assay/analysis Chip	Gold	82.1 g/t	sampling of the three main trenches exposing the main vein yielded up to 21.2 grams per tonne gold over 0.35 metre in trench 3, 82.1 grams per tonne gold over 0.35 metre in trench 2 and 1.6 grams per tonne gold over 1.55 metres in trench 1, while another sample, taken from a site located near the north east shaft, yielded 0.55 gram per tonne gold over 1.5 metres Property File - I.M. Watson [1986-12-09]: Letter Re: Referendum Property Sampling/Drilling Programme 1986
SHAFT 1986 N	Assay/analysis Chip	Gold	4.3 g/t	Chip sampling of the main vein near the shaft yielded 4.3 grams per tonne gold over 1.65 metres Property File - Snowater Resources Ltd. [1986-10-22]: Report on the Referendum Gold Prospect - 1986

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN 1986	N Assay/analysis Bulk Sample	Gold	3.1 g/t	a bulk sample from the "New" vein is reported to have averaged 3.1 grams per tonne gold Property File - T. Cherry [1986-08-01]: Report - Referendum Mine
VEIN 1981	N Assay/analysis Chip	Gold	0.0700 g/t	Across 0.35 metres of the Referendum vein. Assessment Report 10239.
SHAFT 1980	N Assay/analysis Chip	Gold	1.7 g/t	a chip sample (8261) from the eastern shaft vein yielded 1.7 grams per tonne gold over 20 centimetres Property File - Coffee Creek Resources Inc. [1981-01-07]: Report on the Referendum-Stamp Claims
DUMP 1980	N Assay/analysis Grab	Gold	27.5 g/t	two dump samples (8259 and 8260) yielded 10.5 and 27.5 grams per tonne gold, respectively Property File - Coffee Creek Resources Inc. [1981-01-07]: Report on the Referendum-Stamp Claims