

MINFILE Number:	082FSW177	Name:	REFERENDUM (L.4387)	Status:	Past Producer
------------------------	-----------	--------------	---------------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH			Gold	78.1 g/t	a sample containing quartz with banded tourmaline from a trench at the Referendum property
2012	N	Assay/analysis Rock			V STOCKWATCH, October 19, 2012
OUTCROP			Gold	1.80 g/t	grab samples from outcrop
		Assay/analysis	Copper	4.24 %	Assessment Report 27948
2005	N	Grab			
DRILLHOLE			Copper	0.252 %	
		Assay/analysis	Gold	0.86 g/t	Assessment Report 27948
2005	N	Drill Core			
DUMP			Gold	12.9 g/t	a grab sample of dump material from the second shaft, to the north east
1986	N	Assay/analysis Grab			Property File - Snowater Resources Ltd. [1986-10-22]: Report on the Referendum Gold Prospect - 1986
NO. 2 VEIN			Gold	8.6 g/t	Sampling, later that year, of the no. 2 vein yielded up to 82.1 grams per tonne gold over 33 centimetres, with an average of 8.6 grams per tonne gold across 30 centimetres and over a strike length of 30 metres
1986	N	Assay/analysis Chip			Property File - Snowater Resources Ltd. [1987-03-10]: Report on the Referendum Gold Prospect - 1987
NO. 3 VEIN			Gold	36.9 g/t	samples from the no. 3 vein yielded up to 36.9 grams per tonne gold over 20 centimetres
1986	N	Assay/analysis Chip			Property File - Snowater Resources Ltd. [1987-03-10]: Report on the Referendum Gold Prospect - 1987
TRENCHES			Gold	82.1 g/t	sampling of the three main trenches exposing the main vein yielded up to 21.2 grams per tonne gold over 0.35 metre in trench 3, 82.1 grams per tonne gold over 0.35 metre in trench 2 and 1.6 grams per tonne gold over 1.55 metres in trench 1, while another sample, taken from a site located near the north east shaft, yielded 0.55 gram per tonne gold over 1.5 metres
1986	N	Assay/analysis Chip			Property File - I.M. Watson [1986-12-09]: Letter Re: Referendum Property Sampling/Drilling Programme 1986
SHAFT			Gold	4.3 g/t	Chip sampling of the main vein near the shaft yielded 4.3 grams per tonne gold over 1.65 metres
1986	N	Assay/analysis Chip			Property File - Snowater Resources Ltd. [1986-10-22]: Report on the Referendum Gold Prospect - 1986

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN			Gold	3.1 g/t	a bulk sample from the "New" vein is reported to have averaged 3.1 grams per tonne gold
1986	N	Assay/analysis Bulk Sample			Property File - T. Cherry [1986-08-01]: Report - Referendum Mine
VEIN			Gold	0.0700 g/t	Across 0.35 metres of the Referendum vein.
1981	N	Assay/analysis Chip			Assessment Report 10239.
SHAFT			Gold	1.7 g/t	a chip sample (8261) from the eastern shaft vein yielded 1.7 grams per tonne gold over 20 centimetres
1980	N	Assay/analysis Chip			Property File - Coffee Creek Resources Inc. [1981-01-07]: Report on the Referendum-Stamp Claims
DUMP			Gold	27.5 g/t	two dump samples (8259 and 8260) yielded 10.5 and 27.5 grams per tonne gold, respectively
1980	N	Assay/analysis Grab			Property File - Coffee Creek Resources Inc. [1981-01-07]: Report on the Referendum-Stamp Claims