MINFILE Number: 082FSW303 **Name:** ROOT **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP 2004 N	Assay/analysis Grab	Gold Copper	4.34 g/t 0.31 %	a grab sample from the dump of massive pyrrhotite/chalcopyrite mineralization Assessment Report 27738
MAIN 1997 N	Assay/analysis Rock	Gold Copper Cobalt	92.4 g/t 0.34 % 0.2 %	samples from the Root zone are reported to have yielded up to 92.4 grams per tonne gold, 0.2 per cent cobalt and 0.34 per cent copper Property File - Paul Wilton [1998-01-09]: Weekly Report - January 9th 1998 - Connor
ROADCUT 1997 N	Assay/analysis Rock	Zinc Lead Copper Cobalt Nickel Gold	5.7 % 1.0 % 0.3 % 0.35 % 0.09 % 0.5 g/t	samples from road cuts returned values up to 5.7 per cent zinc, 1 per cent lead, 0.3 per cent copper, 0.35 per cent cobalt, 0.09 per cent nickel and 0.5 gram per tonne gold Eagle Plains Resources Ltd. Website, February, 1999
OUTCROP 1985 N	Assay/analysis Chip	Gold	6.8 g/t	surface samples from the root zone were reported to average 6.8 grams per tonne gold over a width of 6 metres and up to 34.9 grams per tonne gold, 10.9 grams per tonne silver and 0.21 per cent copper over 0.9 metre Property File - Davidson, A. J. [1985-09-11]: Root Gold Copper Prospect, Nelson MD
SHAFT 1984 N	Assay/analysis Drill Core	Gold	5.8 g/t	hole (84-5) intercepted a mineralized zone below the shaft yielding 5.8 grams per tonne gold over 0.75 metre Property File - Davidson, A. J. [1985-09-11]: Root Gold Copper Prospect, Nelson MD
SHOWING 1984 N	Assay/analysis Drill Core	Gold	12.4500 g/t	The sample width is 10 centimetres. No other metals were assayed for. Drill hole 84-4. Assessment Report 12937.
TRUE FISSURE 1927 N	Assay/analysis Chip	Gold Silver Lead Zinc	4.11 g/t 6982.84 g/t 15.3 % 32 %	A sample across 0.06 metre on the surface assayed 4.11 grams per tonne gold, 6982.84 grams per tonne silver, 15.3 per cent lead and 32 per cent zinc Minister of Mines Annual Report 1927, page 318