

| | | | | | |
|------------------------|-----------|--------------|--------|----------------|---------|
| MINFILE Number: | 082FSW356 | Name: | DEBBIE | Status: | Showing |
|------------------------|-----------|--------------|--------|----------------|---------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------------|-----------|------------|---|
| 1988 | N | Assay/analysis Drill Core | Silver | 5.5000 g/t | Drill hole 88-3, sample contained a stockwork in sheared dacite over 61 centimetres. Assessment Report 19435. |
| | | | Gold | 3.6300 g/t | |
| | | | Copper | 0.2000 % | |
| 1988 | N | Assay/analysis Drill Core | Gold | 3.6 g/t | Another drill intercept of 3.6 grams per tonne gold with 1 per cent copper over 1.5 metres was also reported Property File - GCNL [1988-10-19]: No. 201 (1988) - Spanish, Debbie, Thorn, Meridor |
| | | | Copper | 1 % | |
| 1988 | N | Assay/analysis Grab | Gold | 7.2 g/t | Assessment Report 19435 |
| | | | | | |
| 1986 | N | Assay/analysis Chip | Gold | 11.4 g/t | two chip samples (DBD09 and DBD14) of leached massive sulphides yielded 10.7 and 11.4 grams per tonne gold over 0.3 and 0.6 metres, respectively Property File - Bullion Range Exploration [1987-09-22]: Prospectus Report on the Debbie Claim |
| | | | | | |
| 1986 | N | Assay/analysis Grab | Gold | 33.6 g/t | a grab sample (4446) of pyrite in altered rock Property File - Bullion Range Exploration [1987-09-22]: Prospectus Report on the Debbie Claim |
| | | | Silver | 52.0 g/t | |
| 1984 | N | Assay/analysis Grab | Gold | 34.28 g/t | samples from the adit assayed from 27.4 to 34.28 grams per tonne gold Assessment Report 12139 |
| | | | | | |