

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
WORKINGS 2006	N	Assay/analysis Rock	Gold Copper	10.506 g/t 1 %	three samples (RP-61 to -63) from former workings yielded from 2.463 to 10.506 grams per tonne gold with 0.027 to greater than 1 per cent copper Assessment Report 28996
VEIN 1988	N	Assay/analysis Rock	Gold	17.1 g/t	a sample from the mineralized zone west of the pulaskite dike over 0.15 metre Assessment Report 18310
VEIN 1986	N	Assay/analysis Chip	Gold Silver	4.10 g/t 20.5 g/t	, a sample (6242) of the mineralized vein across 0.6 metre Assessment Reports 15457 and 18310
VEIN 1986	N	Assay/analysis Chip	Gold Silver	1.0 g/t 3.1 g/t	sample (6243) across 1.4 metres of vein and wallrock with disseminated sulphides Assessment Reports 15457 and 18310
PIT 1986	N	Assay/analysis Chip	Gold Silver	2.7 g/t 7.9 g/t	sample (6244) from the south western pit over 1.5 metres Assessment Report 18310