

<b>MINFILE Number:</b> 082FSW361	<b>Name:</b> CAM 2	<b>Status:</b> Showing
----------------------------------	--------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
WORKINGS		Gold	10.506 g/t	three samples (RP-61 to -63) from former workings yielded from 2.463 to 10.506 grams per tonne gold with 0.027 to greater than 1 per cent copper Assessment Report 28996
2006	Assay/analysis Rock	Copper	1 %	
VEIN		Gold	17.1 g/t	a sample from the mineralized zone west of the pulaskite dike over 0.15 metre Assessment Report 18310
1988	Assay/analysis Rock			
VEIN		Gold	4.10 g/t	, a sample (6242) of the mineralized vein across 0.6 metre Assessment Reports 15457 and 18310
1986	Assay/analysis Chip	Silver	20.5 g/t	
VEIN		Gold	1.0 g/t	sample (6243) across 1.4 metres of vein and wallrock with disseminated sulphides Assessment Reports 15457 and 18310
1986	Assay/analysis Chip	Silver	3.1 g/t	
PIT		Gold	2.7 g/t	sample (6244) from the south western pit over 1.5 metres Assessment Report 18310
1986	Assay/analysis Chip	Silver	7.9 g/t	