

MINFILE Number:	082GNW057	Name:	JOLLY-MOLLY	Status:	Showing
------------------------	-----------	--------------	-------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN			Copper	1.31 %	a sample (no. 710M) from a massive
		Assay/analysis	Molybdenum	0.06 %	pyrrhotite-chalcopyrite vein
1979	N	Rock			Property File - Esperanza Explorations Ltd. [1980-03-01]: Property Examination Report - The Mt. Haley Prospect
DUMP			Copper	0.131 %	a dump sample of monzonite hosting disseminated
		Assay/analysis	Molybdenum	0.015 %	mineralization
1979	N	Grab	Tungsten	0.01 %	Property File - Esperanza Explorations Ltd. [1980-03-01]: Property Examination Report - The Mt. Haley Prospect
OUTCROP			Zinc	0.658 %	a grab sample (B-439) of outcrop assayed 0.658 per
		Assay/analysis			cent zinc, while other talus samples (B-433 to 448)
1975	N	Grab			yielded up to 23.65 per cent zinc and 0.11 per cent copper
					Property File - Aquitaine Co. of Canada Ltd. [1976-02-02]: Report on Southeastern British Columbia Project 1975 for Aquitaine Company of Canada
TRENCH			Copper	1.4 %	chip samples from trench 1 over 55 centimetres from
		Assay/analysis	Silver	41.0 g/t	sample H-3
1974	N	Chip			Property File - R. Sheffield [1974-09-06]: Report - Haley #I
TRENCH			Copper	1.05 %	chip samples from trench 1 over 60 centimetres from
		Assay/analysis	Molybdenum	0.014 %	sample H-1
1974	N	Chip			Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I
TRENCH			Copper	0.80 %	chip samples from trench 1 over 85 centimetres from
		Assay/analysis	Molybdenum	0.003 %	sample H-2
1974	N	Chip			Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I
TRENCH			Copper	1.50 %	chip samples from trench 1 over 95 centimetres from
		Assay/analysis	Molybdenum	0.047 %	sample H-7
1974	N	Chip	Silver	4.8 g/t	Property File - R. Sheffield [1974-09-06]: Report - Haley #I). A select dump sample from one of the former adits yielded 95.8 grams per tonne silver (Property File - R. Sheffield [1974-09-06]: Report - Haley #I